

Performance of Sprayed Polyurethane Foam on Indoor Foundation Walls

INTRODUCTION

More and more owners of existing homes are aware that home comfort and energy efficiency start with insulating basement foundation walls. Most choose traditional insulation methods using fibreglass batts, rigid insulation panels or a combination of these two materials. Homeowners can usually perform the work themselves. Others are choosing a less common, more expensive but more efficient technique—sprayed polyurethane foam insulation. This work must be done by a specialist in the field because it requires highly specialized equipment approved by the insulation's manufacturer.

Research already conducted by Canada Mortgage and Housing Corporation (CMHC) has shown that, for insulating foundation walls from the interior, sprayed polyurethane insulation offered some advantages over traditional insulation, such as its higher thermal resistance per inch of thickness, its greater airtightness, its resistance to air movement and to moisture.

Considering that foundation walls are often exposed to moisture and to water infiltration, there is some concern among construction and renovation stakeholders with regard to the behaviour of the sprayed polyurethane foam over the medium and long term when walls have been insulated from the inside.

SCOPE OF THE RESEARCH

This is an expensive method of insulation. Is there reason to question the long-term performance of sprayed polyurethane foam on interior walls?

In order to shed some light on the question, this research evaluated the performance of spray polyurethane in terms of its efficiency and adhesion durability on different types of foundation walls (poured concrete and stonework) and on the quality of the foam five or more years after installation.

METHOD

The research was conducted in accordance with standard protocol:

- setting a credible, representative sample of homes insulated with this product
- following a standardized inspection process

Home sampling and selection were performed in accordance with the following:

- sample of at least 12 homes
- two separate locations: Metropolitan Montréal area and the region of Gatineau
- foundation walls insulated more than five years ago
- walls are of variable composition, some stone foundation and some poured concrete
- full-height basement and crawl spaces

A standard data sheet was used to have a consistent, standardized inspection process from one house to another.

To know whether insulation adhesion might vary from one situation to another, it was important to check if the foundation walls had any water infiltration or moisture caused by poor site drainage, defective eavestroughs, a high water table or any other exterior problem.

Also, it was important to note the type of foundation (poured concrete, stone or cement blocks) in order to determine whether the insulation behaved differently in each of these situations.

Adhesion tests were performed with a specialized instrument to ascertain whether the insulation provided acceptable adhesion to the foundation over time. To do so, two to four tests were performed in each house, at strategic sites:

- primarily in the lower part of the foundation wall (part below ground level), as close as possible to the basement or crawlspace floor
- in the upper part of the foundation wall (part above ground) to determine whether there were behaviour or adhesion differences between the part more exposed to moisture than the less exposed one.

The device used displayed a reading on a dial, expressed in kg, of the tear strength force required to detach the insulation from the foundation wall.

Before the tests, a researcher knocked on all the accessible, insulated wall surfaces to check whether there might be any cavities behind the insulation and to determine the location of the adhesion test sites.



Figure 1 Device used to test tear strength force

FINDINGS

Table 1 below is a summary of the key findings obtained from the 12 houses sampled and visited.

For the two homes in which results were poor (in Laval) and nil (in Outremont), it was obvious that the foundation walls were neither adequate nor in a condition suitable for this type of insulation. Indeed, in the first case, the foundation wall was of poor quality and damp. The owner indicated that the wall was friable and crumbling a bit before the insulation was applied. Therefore, the insulation appears to have been applied to a damp surface resulting in poor adhesion to the foundation. In the second case, the tests failed because the stone foundation had very friable parging. Despite this, the insulation remained well adhered to the walls over time; thus, there were no cavities between the insulation and the foundation walls.

In several homes, the insulation was not protected from fire as required by building codes, since it is a product with a high flame-spread rating. It would seem that installers of this type of insulation do not always advise their clients of this requirement. The insulation should be covered with gypsum or any other acceptable fire-retardant material.

CONCLUSION

Based on the observations and tests performed on the 12 homes in the list, this research seems to confirm the reliability of polyurethane foam sprayed on the inside of foundation walls.

- In terms of adhesion, sprayed polyurethane behaves very well in the medium and long term.
- In terms of homogeneity and rigidity, polyurethane retains its cellular structure.
- The type of foundation wall (cement blocks, stone, poured concrete) does not affect adhesion rate when the insulation is applied under proper conditions, i.e., dry foundation.
- The green or yellow colouring of the insulation (yellow: before 1997 and green: after 1997) does not increase or decrease adhesion quality.
- Polyurethane on the inside wall does not behave differently above or below ground level.
- No separation or cracks occur between the insulation and wooden structural components and other adjacent materials (wooden joists, wooden or steel beams, wooden window frames, etc.).

Based on the poorest finding in Table 1, the insulation requires a minimum tear strength force of 117 kPa to detach it from the wall or to make it let go, while some required up to 248 kPa. These findings substantially exceed applicable standards for this insulation.

According to the homes checked, sprayed polyurethane foam insulation behaves very well in the medium and long term from the perspective of adhesion to foundations and adjacent materials and in terms of its ability to conserve its cellular properties and its homogeneity.

Table I Summary of findings

Location	Type of foundation	Colour of insulation	Thickness of insulation (mm)	Year of inst.	Adhesion test average (kPa)	Cellular structure	
						Homogeneity	Rigidity
Duval St. Laval	Poured concrete	Yellow	25	Before 1991	33	Uniform	Very firm
Dollard St. Hull	Poured concrete	Green	38-44	1998	152	Uniform	Very firm
Champlain St. Hull	Cement blocks	Green	Variable 32-38	1998	124 See Note 1	Uniform	Very firm
Rodolphe St. Gatineau	Stone	Yellow	Variable 32-70	1998	145 See Note 1	Uniform	Very firm
Angèle St. Bellefeuille	Poured concrete	Yellow	Variable 44-63	1994	248	Uniform	Very firm
Marcil St. Laval	Poured concrete	Yellow	50	1996	7 See Note 2	Uniform	Very firm
Précourt St. St-Jérôme	Poured concrete	Yellow	Variable 30-50	+ 20 yrs	172	Uniform	Very firm
le Mesurier St. Montréal	Poured concrete	Yellow	Variable 32-63	1994	179	Uniform	Very firm
Cr. Louise St. Mascouche	Poured concrete	Yellow	Variable 19-25	1996	117	Uniform	Very firm
Chris-Ida St. Mascouche	Poured concrete	Green	63	1997	214	Uniform	Very firm
Maplewood St. Outremont, Mtl.	Stone	Yellow	50	+ 10 yrs	See Note 3	Uniform	Very firm
Lambert St. Oka	Poured concrete	Green	50	1998	152	Uniform	Very firm

Note 1

Although these are stone or cement block foundations, insulation adhesion is very good.

Note 2

Out of all the houses tested, only this house obtained poor results. The foundation wall is of inferior quality and wet. The owner indicated that the wall was friable and crumbling a bit before the insulation was applied. The insulation therefore seems to have been applied on a damp surface, resulting in poor adhesion to the foundation.

Note 3

The tests failed because the stone foundation had a very friable cement parging. Nevertheless, the insulation remained well-adhered to the walls; thus, there were no cavities between the insulation and the foundation walls.

CMHC Project Manager: Don Fugler

Consultant: Consul-Tech JCF

Housing Research at CMHC

Under Part IX of the *National Housing Act*, the Government of Canada provides funds to CMHC to conduct research into the social, economic and technical aspects of housing and related fields, and to undertake the publishing and distribution of the results of this research.

This fact sheet is one of a series intended to inform you of the nature and scope of CMHC's research.

To find more *Research Highlights* plus a wide variety of information products, visit our website at

www.cmhc.ca

or contact:

Canada Mortgage and Housing Corporation
700 Montreal Road
Ottawa, Ontario
K1A 0P7

Phone: 1-800-668-2642

Fax: 1-800-245-9274

©2004, Canada Mortgage and Housing Corporation
Printed in Canada
Produced by CMHC
Revised: 2005, 2010

26-01-10

Although this information product reflects housing experts' current knowledge, it is provided for general information purposes only. Any reliance or action taken based on the information, materials and techniques described are the responsibility of the user. Readers are advised to consult appropriate professional resources to determine what is safe and suitable in their particular case. Canada Mortgage and Housing Corporation assumes no responsibility for any consequence arising from use of the information, materials and techniques described.