



Government
of Canada

Gouvernement
du Canada

Canadian General
Standards Board

Office des normes
générales du Canada

CAN/CGSB-3.23-2016

Supersedes CAN/CGSB-3.23-2011

National Standard of Canada

Aviation turbine fuel (Grades JET A and JET A-1)

Canadian General Standards Board **CGSB**



Standards Council of Canada
Conseil canadien des normes

Canada

Experience and excellence

Expérience et excellence



The CANADIAN GENERAL STANDARDS BOARD (CGSB), under whose auspices this standard has been developed, is a government agency within Public Services and Procurement Canada. CGSB is engaged in the production of voluntary standards in a wide range of subject areas through the media of standards committees and the consensus process. The standards committees are composed of representatives of relevant interests including producers, consumers and other users, retailers, governments, educational institutions, technical, professional and trade societies, and research and testing organizations. Any given standard is developed on the consensus of views expressed by such representatives.

CGSB has been accredited by the Standards Council of Canada as a national standards-development organization. The standards that it develops and offers as National Standards of Canada conform to the criteria and procedures established for this purpose by the Standards Council of Canada. In addition to standards it publishes as National Standards of Canada, CGSB produces standards to meet particular needs, in response to requests from a variety of sources in both the public and private sectors. Both CGSB standards and CGSB national standards are developed in conformance with the policies described in the CGSB Policy and Procedures Manual for the Development and Maintenance of Standards.

CGSB standards are subject to review and revision to ensure that they keep abreast of technological progress. CGSB will initiate the review of this standard within five years of the date of publication. Suggestions for their improvement, which are always welcome, should be brought to the notice of the standards committees concerned. Changes to standards are issued either as separate amendment sheets or in new editions of standards.

An up-to-date listing of CGSB standards, including details on latest issues and amendments, and ordering instructions, is found in the CGSB Catalogue at our Web site — www.tpsgc-pwgsc.gc.ca/ongc-cgsb/index-eng.html along with more information about CGSB products and services.

Although the intended primary application of this standard is stated in its Scope, it is important to note that it remains the responsibility of the users of the standard to judge its suitability for their particular purpose.

The testing and evaluation of a product against this standard may require the use of materials and/or equipment that could be hazardous. This document does not purport to address all the safety aspects associated with its use. Anyone using this standard has the responsibility to consult the appropriate authorities and to establish appropriate health and safety practices in conjunction with any applicable regulatory requirements prior to its use. CGSB neither assumes nor accepts any responsibility for any injury or damage that may occur during or as the result of tests, wherever performed.

Attention is drawn to the possibility that some of the elements of this Canadian standard may be the subject of patent rights. CGSB shall not be held responsible for identifying any or all such patent rights. Users of this standard are expressly advised that determination of the validity of any such patent rights is entirely their own responsibility.

Language

In this Standard, “shall” states a mandatory requirement, “should” expresses a recommendation and “may” is used to express an option or that which is permissible within the limits of this Standard. Notes accompanying clauses do not include requirements or alternative requirements; the purpose of a note accompanying a clause is to separate from the text explanatory or informative material. Annexes are designated normative (mandatory) or informative (non-mandatory) to define their application.

Further information on CGSB and its services and standards may be obtained from:

The Manager
Standards Division
Canadian General Standards Board
Gatineau, Canada
K1A 1G6

A National Standard of Canada is a standard developed by an SCC-accredited Standards Development Organization (SDO), and approved by the Standards Council of Canada (SCC), in accordance with SCC’s: *Requirements and Guidance-Accreditation for Standards Development Organizations, and Requirements and Guidance-Approval of National Standards of Canada Designation*. More information on National Standard requirements can be found at www.scc.ca.

An SCC-approved standard reflects the consensus of a number of experts whose collective interests provide, to the greatest practicable extent, a balance of representation of affected stakeholders. National Standards of Canada are intended to make a significant and timely contribution to the Canadian interest.

SCC is a Crown corporation within the portfolio of Industry Canada. With the goal of enhancing Canada’s economic competitiveness and social well-being, SCC leads and facilitates the development and use of national and international standards. SCC also coordinates Canadian participation in standards development, and identifies strategies to advance Canadian standardization efforts. Accreditation services are provided by SCC to various customers, including product certifiers, testing laboratories, and standards development organizations. A list of SCC programs and accredited bodies is publicly available at www.scc.ca.

Users should always obtain the latest edition of a National Standard of Canada from the standards development organization responsible for its publication, as these documents are subject to periodic review.

The responsibility for approving standards as NSCs rests with:

Standards Council of Canada
55 Metcalfe Street, Suite 600
Ottawa, Ontario K1P 6L5, CANADA

How to order **CGSB** Publications:

- by telephone — 819-956-0425 *or*
— 1-800-665-2472
- by fax — 819-956-5740
- by mail — CGSB Sales Centre
Gatineau, Canada
K1A 1G6
- in person — Place du Portage
Phase III, 6B1
11 Laurier Street
Gatineau, Quebec
- by email — ncr.cgsb-ongc@tpsgc-pwgsc.gc.ca
- on the Web — www.tpsgc-pwgsc.gc.ca/ongc-cgsb/index-eng.html

NATIONAL STANDARD OF CANADA

CAN/CGSB-3.23-2016

Supersedes CAN/CGSB-3.23-2011

Aviation turbine fuel (Grades JET A and JET A-1)

CETTE NORME NATIONALE DU CANADA EST DISPONIBLE EN VERSIONS
FRANÇAISE ET ANGLAISE.

ICS 75.160.20

Published November 2016 by the
Canadian General Standards Board
Gatineau, Canada K1A 1G6

© HER MAJESTY THE QUEEN IN RIGHT OF CANADA,
as represented by the Minister of Public Services and Procurement,
the Minister responsible for the Canadian General Standards Board (2016).

No part of this publication may be reproduced in any form without the prior permission of the publisher.

CANADIAN GENERAL STANDARDS BOARD

Committee on Aviation Fuels

(Voting membership at date of approval)

Chair

Poitras, P. National Defence (User)

General interest category

Hanganu, A. Inspectorate Canada
MacLean, G. Intertek Commodities Division
Pama, M. Certispec Services Inc.
Pickard, A. L. Consultant
Tharby, R. D. Tharby Technology, Consultants
Wispinski, D. Alberta Innovates – Technology Futures

Producer category

Burgazli, J. Innospec Inc.
Camp, K. Imperial Oil Ltd.
Conn, A. Ethyl Corporation
Geoffroy, L. Valero Energy Corporation
Gropp, R. GE Water and Process Technologies
Mitchell, K. Shell Canada Ltd.
Munroe, D. Suncor Energy Inc.
Titus, J. Irving Oil Ltd.

Regulator category

Bilcock, D. Transport Canada

User category

Brar, C. Air Canada
Briggs, D. Government of the Northwest Territories
Cooper, S. Government of Nunavut
Day, T. WestJet Airlines Ltd.
MacLeod, B. Public Services and Procurement Canada
Waddleton, D. Pratt & Whitney Canada Corporation

Secretary (non-voting)

Schuessler, M. Canadian General Standards Board

Acknowledgment is made for the translation of this National Standard of Canada by the Translation Bureau of Public Services and Procurement Canada.

Contents		Page
1	Scope	1
2	Normative references	1
3	Classification	3
4	General fuel requirements	3
5	Detailed requirements	3
6	Additive requirements	8
7	Inspection	10
8	Options	10
9	Precautions	10
Annex A (normative) Referenced ASTM International Publications		13

Aviation turbine fuel (Grades JET A and JET A-1)

1 Scope

This standard applies to two grades of kerosene-type aviation turbine fuel (grades JET A and JET A-1), consisting of conventional hydrocarbons, synthetic hydrocarbons, naturally occurring non-hydrocarbons and additives as specified herein.

The fuels are normally used in civil aviation operations. The two grades differ only in freezing point. Grade JET A has a maximum freezing point of -40°C and Grade JET A-1 has a maximum freezing point of -47°C . Kerosene-type aviation turbine fuels are distillates with a minimum flash point of 38°C .

Limitations for use — Aircraft operators should consult their aircraft manuals for the type of fuel, fuel additives and any temperature-related or other limitations.

Temperature limitations — When temperatures are close to the fuel freezing point, fuel operability problems can be experienced. JET A, with a specification freezing point of -40°C , is not intended for use during extremely cold weather conditions or when the ambient temperature is close to, or below, -40°C . It also requires more restrictive use than JET A-1. For more information concerning temperature limitations, see Transport Canada's Airworthiness Notice No. B021 (par. 2.2) and 9.3 in this standard.

The testing and evaluation of a product against this standard may require the use of materials and/or equipment that could be hazardous. This document does not purport to address all the safety aspects associated with its use. Anyone using this standard has the responsibility to consult the appropriate authorities and to establish appropriate health and safety practices in conjunction with any applicable regulatory requirements prior to its use.

2 Normative references

The following normative documents contain provisions that, through reference in this text, constitute provisions of this National Standard of Canada. The referenced documents may be obtained from the sources noted below.

NOTE The addresses provided below were valid at the date of publication of this standard.

An undated reference is to the latest edition or revision of the reference or document in question, unless otherwise specified by the authority applying this standard. A dated reference is to the specified revision or edition of the reference or document in question.

2.1 Canadian General Standards Board (CGSB)

CAN/CGSB-3.524 — *Biodiesel (B100) for blending in middle distillate fuels.*

2.1.1 Source

The above may be obtained from the Canadian General Standards Board, Sales Centre, Gatineau, Canada K1A 1G6. Telephone 819-956-0425 or 1-800-665-2472. Fax 819-956-5740. E-mail ncr.cgsb-ongc@tpsgc-pwgsc.gc.ca. Web site www.tpsgc-pwgsc.gc.ca/ongc-cgsb/index-eng.html.

2.2 Transport Canada (TC)

Airworthiness Notice No. B021 — *Low Temperature Operations with JET A Fuel.*

2.2.1 Source

The above may be obtained from the Department of Transport, Transport Dangerous Goods Directorate, Ottawa, Canada K1A 0N5, or Web site www.tc.gc.ca.

2.3 ASTM International

Annual Book of ASTM Standards (see Annex A).

2.3.1 Source

The above may be obtained from ASTM International, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959, U.S.A., telephone 610-832-9585, fax 610-832-9555, Web site www.astm.org, or from IHS Markit, 200-1331 MacLeod Trail SE, Calgary, Alberta T2G 0K3, telephone 613-237-4250 or 1-800-267-8220, fax 613-237-4251, Web site www.global.ihs.com.

2.4 Energy Institute (EI)

IP 540 — *Determination of the existent gum content of aviation turbine fuel — Jet evaporation method*

IP 583 — *Determination of the fatty acid methyl esters content of aviation turbine fuel using flow analysis by Fourier transform infrared spectroscopy — Rapid screening method*

IP 585 — *Determination of fatty acid methyl esters (FAME), derived from bio-diesel fuel, in aviation turbine fuel — GC-MS with selective ion monitoring/scan detection method*

IP 590 — *Determination of fatty acid methyl esters (FAME) in aviation turbine fuel — HPLC evaporative light scattering detector method*

IP 599 — *Determination of fatty acid methyl esters (FAME) in aviation turbine fuel — Gas Chromatography using heart-cut and refocusing.*

2.4.1 Source

The above may be obtained from the Energy Institute, 61 New Cavendish Street, London, England W1G 7AR, UK, telephone +44 (0)20-7467-7100, fax +44 (0)20-7255-1472, e-mail pubs@energyinst.org.uk, Web site www.energyinst.org.uk.

2.5 European Committee for Standardization (CEN)

EN 14214 — *Liquid petroleum products — Fatty acid methyl esters (FAME) for use in diesel engines and heating applications — Requirements and test methods.*

2.5.1 Source

The above may be obtained from BSI Shop at <http://www.bsigroup.com/>.

2.6 U.S. Department of Defense

MIL-PRF-25017 — *Inhibitor, Corrosion/Lubricity Improver, Fuel Soluble*

QPL-25017 — *Qualified Products List of Products Qualified Under Performance Specification MIL-PRF-25017 Inhibitor, Corrosion/Lubricity Improver, Fuel Soluble.*

2.6.1 Source

The above may be obtained from Document Automation and Production Service, 700 Robbins Avenue, Building 4/D, Philadelphia, PA 19111-5094, U.S.A. Fax 215-697-1462, Web site <http://quicksearch.dla.mil/>

3 Classification

3.1 The kerosene-type aviation turbine fuel shall be classified in the following grades (see 8.1).

3.1.1 Grades

JET A

JET A-1.

4 General fuel requirements

4.1 Conventional hydrocarbons shall be predominantly petroleum-derived from natural gas liquid condensates, crude oil and heavy oil, including bitumen from oil sands.

4.2 Synthetic hydrocarbons shall consist predominantly of hydrocarbons derived from non-petroleum sources such as biomass, natural gas, coal, fats and oils by processes such as gasification, reforming, Fischer-Tropsch synthesis, and hydroprocessing or hydrocracking. Synthesized paraffinic kerosene (SPK) is the name given to synthetic blending components.

4.2.1 Synthetic hydrocarbons are only permitted in jet fuel in a blend with conventional hydrocarbons. The synthetic component and blending requirements shall meet ASTM D7566. Once a batch of aviation turbine fuel containing synthetic hydrocarbons is manufactured, blended and released to the specifications of CAN/CGSB-3.23 then the extended requirements specified in 5.14 are no longer applicable. Any re-testing shall be done to the requirements of CAN/CGSB-3.23 excluding 5.14.

4.3 The fuel shall be visually clear and free from undissolved water and particulate matter.

4.4 The odour of the fuel should not be nauseating or irritating.

5 Detailed requirements

5.1 The detailed requirements shall apply to the fuel unless otherwise specified.

5.2 Except as described in 4.2.1, the fuel shall comply with the detailed requirements specified in 5.4 to 5.13, using the test methods indicated. The specified limiting values shall not be changed. This precludes any allowances for the test method precision and adding or subtracting digits.

5.2.1 A batch of fuel which includes synthetic hydrocarbons shall also comply with 5.14 the first time it is tested for compliance with this specification.

5.3 To determine conformance with the specified limiting values, an observed value or a calculated values shall be rounded off "to the nearest unit" in the last right-hand digit used in expressing the specified limiting values, in accordance with the rounding-off method of ASTM E29. There are two exceptions (see 5.5.1 and 5.5.4) that shall be reported to the nearest 0.5°C.

5.3.1 Where test values differ between two parties, a resolution shall be in accordance with ASTM D3244 in order to determine conformance with the specified limiting values, with the criticality of the limits set as $P = 0.5$.

	Property	Specified limiting values		
		JET A or JET A-1		Test method
		Min.	Max.	ASTM
5.4	Composition			
5.4.1	Acidity, total, mg KOH/g	—	0.10	D3242
5.4.2	Aromatics, % by volume	—	25	D1319 ^a
		—	26.5	D6379
5.4.3	Sulphur, total, % by mass (see 5.15)	—	0.30	D2622, D4294 ^a , D5453 or D7039
5.4.4	Sulphur, mercaptan ^b			
	a) % by mass or	—	0.003	D3227
	b) Doctor test	negative		D4952
5.5	Volatility			
5.5.1	Distillation temperature, °C	—	—	D86 ^a or D2887 ^c
	a) Initial boiling point	Report		
	b) 10% recovered (T10)	—	205	
	c) 50% recovered (T50)	Report		
	d) 90% recovered (T90)	Report		
	e) Final boiling point	—	300	
5.5.2	Residue ^d , % by volume	—	1.5	D86
5.5.3	Loss ^d , % by volume	—	1.5	D86
5.5.4	Flash point, °C	38	—	D56 ^a or D3828 ^e
5.5.5	Density at 15°C, kg/m ³	775	840	D1298 ^a or D4052
5.6	Fluidity			
5.6.1	Freezing point, °C (see 9.3)	—	-40 (JET A) -47 (JET A-1)	D2386 ^f or D5972 ^a

	Property	Specified limiting values		
		JET A or JET A-1		Test method
		Min.	Max.	ASTM
5.6.2	Kinematic viscosity ^g at -20°C, mm ² /s (see 9.3)	—	8.0	D445 ^a or D7042
5.7	Combustion			
5.7.1	a) Smoke point, mm or	25	—	D1322
	b) Smoke point, mm and	18	—	D1322
	Naphthalenes, % by volume	—	3.0	D1840
5.7.2	Net heat of combustion, MJ/kg	42.8	—	D4529 ^h , D3338 ^h or D4809 ^a
5.8	Corrosion (see 6.6 and 9.6)			
5.8.1	Copper strip corrosion, 2 h at 100 °C	—	No. 1	D130
5.9	Thermal stability ⁱ (see 9.2.2)			
5.9.1	Filter pressure drop, mm Hg	—	25	D3241
5.9.2	Tube deposit	Less than 3		D3241
5.9.3	Visual examination, on the heater tube, darkest deposits	No peacock (rainbow) or abnormal colour deposits		D3241
5.10	Contaminants (see 9.7)			
5.10.1	Existent gum, mg/100 mL	—	7	D381 ^a (steam jet) or Energy Institute IP 540 (air or steam jet)
5.10.2	Particulate matter, mg/L at time of delivery to	—		D2276 or D5452 ^j
	a) Purchaser's storage	—	2.2	
	b) Aircraft and refuellers	—	0.44	
5.11	Water separation characteristics (see 9.5) Micro-separometer ^k rating, a) or b)			
	a) Before or after addition of static dissipator additive (see 6.2).	85	—	D7224 ^a

Property	Specified limiting values		
	JET A or JET A-1		Test method
	Min.	Max.	ASTM
b) after addition of static dissipator additive (see 6.2)	70	—	D3948
5.12 Electrical conductivity (see 6.2)			
5.12.1 At point, time and temperature of delivery, pS/m	50	600	D2624
5.13 Additives (see 9.6)			
5.13.1 Static dissipator additive (see 6.2), mg/L			
a) Original addition	—	3	—
b) Cumulative	—	5	—
5.13.2 Antioxidant (see 6.3), mg/L Optional	—	24	—
5.13.3 Metal deactivator (see 6.4), mg/L Optional	—	5.7	—
5.13.4 Fuel system icing inhibitor (see 6.5), % by volume Optional	0.10	0.15	D5006
5.13.5 Corrosion inhibitor/lubricity improver (see 6.6) Optional			
5.13.6 Leak detection additive (see 6.7), mg/kg Optional	—	1	—
5.14 Extended requirements for fuels containing synthetic hydrocarbons ^l (see 4.2.1)			
5.14.1 Synthetic hydrocarbon content ^m , % by volume	—	50	—
5.14.2 Aromatics ⁿ , % by volume			
a) or	8	—	D1319 ^a
b)	8.4	—	D6379

	Property	Specified limiting values		
		JET A or JET A-1		Test method
		Min.	Max.	ASTM
5.14.3	Distillation temperature differences ^o , °C			D2887 ^c or D86 ^a
	a) T50-T10	15	—	
	b) T90-T10	40	—	
5.14.4	Lubricity, at point of manufacture, mm (see 9.1)	—	0.85	D5001
<p>^a In the event of a dispute, this method shall be the referee method.</p> <p>^b The mercaptan sulphur determination may be waived if the fuel is considered “sweet”, and receives a negative result by the doctor test described in ASTM D4952.</p> <p>^c When testing in accordance with ASTM D2887, apply the relevant Annex to convert distillation temperature results to estimates of ASTM D86 results.</p> <p>^d If ASTM D2887 is used to determine distillation temperature (see 5.5.1), then residue and loss requirements shall not apply because no residue or loss results from the application of ASTM D2887.</p> <p>^e The results obtained by ASTM D3828 can be up to 2°C lower than those obtained by ASTM D56, which is the referee method.</p> <p>^f CAUTION: Results from two extensive round-robin tests reported in ASTM Research Reports 1536 and 1572 demonstrated that the manual freezing point test ASTM D2386 could only detect heavy material contamination (e.g. diesel fuel) in JET A and JET A-1 fuels in less than half of the cases tested, whereas the automatic freezing point test ASTM D5972 was effective at detecting such contamination in all cases tested.</p> <p>^g The SI unit for kinematic viscosity is the square metre per second. The preferred multiple for fluids in this viscosity range is the square millimetre per second, which is equivalent to a centiStokes (i.e., 1 mm²/s = 1 cSt).</p> <p>^h Calculate and report the net heat of combustion corrected for the sulphur content when using these empirical test methods</p> <p>ⁱ Thermal stability shall be determined using the Jet fuel Thermal Oxidation Tester at a minimum heater-tube-controlled temperature of 260°C. The SI unit equivalent for the pressure differential is 3.3 kPa. However, the Jet Fuel Thermal Oxidation Tester gives the results in mm Hg, and 25 mm Hg is the exact maximum.</p> <p>^j ASTM D2276 and D5452 refer to different sampling procedures. In some situations it may not be practical to sample according to D2276; however, when results are obtained by both methods, D2276 shall be considered the referee method.</p> <p>^k The minimum micro-separometer (MSEP) rating applies from the point of manufacture to the point immediately before the fuel enters dedicated transportation to airport storage. MSEP by ASTM D7224 can be useful in determining the water separation characteristics of a batch of jet fuel even when additized with static dissipator additive and certain other additives that do not actually degrade water separation performance in coalescing separators. When the fuel enters dedicated transportation to airport storage, or when the fuel is already in airport storage, the MSEP rating requirement shall not apply. When a fuel system icing inhibitor (see 6.5) or a corrosion inhibitor/lubricity improver (see 6.6) is added, the MSEP limits apply before its addition. For clarity MSEP results shall be reported by test method (i.e. MSEP by ASTM D3948 or MSEP by ASTM D7224). Conductivity often drops during fuel distribution due to additive depletion and lower temperatures, as noted the limits also apply at point of use.</p>				

Property	Specified limiting values		
	JET A or JET A-1		Test method
	Min.	Max.	ASTM
<p>^l The synthetic hydrocarbon content, aromatics, distillation slope, and lubricity criteria only apply to aviation turbine fuels produced to this specification that contain synthetic hydrocarbons. The criteria do not apply to aviation turbine fuels produced to CAN/CGSB-3.23 specifications from conventional hydrocarbons and that do not contain synthesized hydrocarbons. The criteria are also not applicable to aviation turbine fuels containing synthesized hydrocarbons after the fuels have been manufactured, blended and released to CAN/CGSB-3.23.</p> <p>^m The synthetic hydrocarbon content of the blend shall be calculated from metered (measured) volumes used to prepare the blend. Lower maximum limit may apply as per ASTM D7566.</p> <p>ⁿ Minimum aromatics content limits are based on current experience with synthetic fuels, and these values were established from what is typical for jet fuel produced from conventional hydrocarbons.</p> <p>^o The distillation slope limits are based on current experience with synthetic fuels, and these values were established from what is typical for jet fuel produced from conventional hydrocarbons.</p>			

5.15 Sulphur

The accuracy of ASTM D7039 for the sulphur content of jet fuel beyond 2822 mg/kg sulphur has not been validated. Users are cautioned to conduct their own validation when using this test method for jet fuel containing more than 2822 mg/kg sulphur.

6 Additive requirements

6.1 Only the additives listed in 6.2 to 6.7 may be added to the fuel. Refer to 5.13 for specified limiting values and test method for each property. The supplier shall record the amount and names of each additive.

6.1.1 The amount of each additive used in the fuel shall be determined by the test method (see 5.13 and 9.6) or by volume reconciliation. Procedures for volume reconciliation should include recording the volume of additive introduced to the fuel and the volume of fuel additized in appropriate units.

6.2 Static dissipator additive (SDA)

6.2.1 Static dissipator additive STADIS® 450¹ shall be added to the fuel to meet the electrical conductivity requirements specified in 5.12.1. The original concentration of the SDA shall not exceed 3 mg/L.

6.2.2 When additive depletion is evident by a conductivity loss, further addition of the SDA is permitted as follows:

- If the original concentration of the SDA is not known, then an original addition of 3 mg/L is assumed and further addition of SDA shall not exceed 2 mg/L.
- The cumulative concentration of the SDA shall not exceed 5 mg/L.

¹ STADIS® 450, a registered trademark of Innospec Fuel Specialties LLC, is manufactured in the United States and distributed globally by Innospec Fuel Specialties LLC.

6.2.3 Electrical conductivity varies with temperature. A typical relationship follows:

$$\log k_t = a(t - t_1) + \log k_{t_1}$$

where:

k_t = electrical conductivity at temperature t , °C

k_{t_1} = electrical conductivity at temperature t_1 , °C

a = a factor that depends on fuel composition but normally is within the range 0.013 to 0.018 for kerosene-type aviation turbine fuels

6.2.3.1 The temperature-conductivity factor, a , increases at or below an approximate temperature of -10°C. For conductivity at very low temperatures, it is recommended that a separate factor be determined based on actual measurements at the lowest expected temperatures that will be encountered. For more information on how low temperature affects conductivity, see the relevant Appendix of ASTM D2624.

6.3 Antioxidants

Only the following antioxidants may be added separately or in combination to the fuel. The total concentration (not including mass of solvent) shall not exceed 24 mg/L.

- a) 2,6-di-*tert*-butylphenol
- b) 2,6-di-*tert*-butyl-4-methylphenol
- c) 2-*tert*-butyl-4,6-dimethylphenol (2,4-dimethyl-6-tertiary butylphenol)
- d) 75% minimum, 2,6-di-*tert*-butylphenol,
25% maximum mixture of *tert*- and tri-*tert*-butylphenols
- e) 55% minimum, 2-*tert*-butyl-4, 6-dimethylphenol (2,4-dimethyl-6-tertiary butylphenol)
15% minimum, 2,6-di-*tert*-butyl-4-methylphenol
Remainder as methyl and dimethyl *tert*-butylphenols
- f) 72% minimum 2-*tert*-butyl-4,6-dimethylphenol (2,4-dimethyl-6-tertiary butylphenol) 28% maximum, methyl and dimethyl *tert*-butylphenols.

NOTE The names of the antioxidants conform to the International Union of Pure and Applied Chemistry (IUPAC) naming convention. In some cases, the common name of the antioxidant has been included in brackets after the IUPAC name.

6.4 Metal deactivator additive (MDA)

Only N,N'-disalicylidene-1,2-propane-diamine may be added as a metal deactivator at a concentration not exceeding 2.0 mg/L (not including mass of solvent) on the initial fuel manufactured at the refinery. Higher concentrations are permitted in circumstances where copper contamination is suspected to occur during distribution. Cumulative concentration of metal deactivator when re-treating the fuel shall not exceed 5.7 mg/L (see 9.2).

6.5 Fuel system icing inhibitor

When specified (see 8.1.2) and agreed by the supplier and the purchaser, a fuel system icing inhibitor conforming to ASTM D4171 (Type III [DIEGME]) shall be added to the fuel (see 5.13.4).

6.6 Corrosion inhibitors/lubricity improvers

When specified (see 8.1.2) and agreed by the supplier and the purchaser, a corrosion inhibitor/lubricity improver qualified to U.S. Military Specification MIL-PRF-25017 and listed in the associated qualified product list (QPL) 25017 shall be added to the fuel (see 9.1). The concentration of the additive in the fuel shall be as specified in the QPL, and its introduction into the fuel shall be separate from the addition of other additives.

6.7 Leak detection additive²

Only Tracer A (LDTA-A®)³ may be added as a leak detection additive. The maximum concentration is 1 mg/kg.

7 Inspection

Samples for testing shall be obtained in accordance with ASTM D4057. For automatic sampling ASTM D4177 shall be used.

8 Options

8.1 The following option shall be specified in the application of this standard:

- a) Grade JET A or JET A-1 (see 3.1).

8.2 The following options may be specified in the application of this standard, if required:

- a) Fuel system icing inhibitor (see 6.5)
- b) Corrosion inhibitor/lubricity improver (see 6.6).

9 Precautions

9.1 Lubricity information statement

9.1.1 Lubricity, which is the ability of jet fuel to act as a lubricant for certain aircraft fuel-wetted components, can vary considerably. It depends on the design, materials used and the intrinsic lubricity of the fuel. There have been a number of cases of engine hardware failures directly attributed to poor-lubricity fuel.

² The Tracer Tight methodology to detect and locate leaks in ground-based fuel storage, delivery and dispensing systems does not form part of this standard. Refer to the additive supplier for this information. Praxair Services, Inc. can be contacted at 3755 N. Business Center Drive, Tuscan, AZ 85705, U.S.A., telephone 1-800-989-9929, web site www.praxair.com.

³ Tracer A (LDTA-A®) is a registered trademark of Praxair Services, Inc.

9.1.2 ASTM D5001 may be used to identify the quality of the fuel since this standard does not address the measurement of fuel lubricity. Hydrogen-processing⁴ usually produces fuels with poor lubricity. Blending or commingling with non-hydrogen-processed fuels will improve lubricity, and the use of lubricity-improver additives (corrosion inhibitors) may offer a solution (see 6.6).

9.1.3 Problems are more likely to occur when aircraft operations are confined to a single refinery source where fuel is severely hydrogen-processed and where there is no commingling with fuels from other sources during distribution between refinery and the aircraft.

9.2 Copper information statement

9.2.1 The contamination of jet fuel can occur during manufacture or during distribution in marine vessels with copper coils, and from the copper-alloy components and fittings in sampling points.

9.2.2 Trace levels of copper, in the parts per billion range, can be sufficient to degrade the ASTM D3241 Jet Fuel Thermal Oxidation Tester test result. Where the possibility of copper pickup is suspected, an approved metal deactivator as specified in 6.4 may be added to preserve or restore the thermal stability of the fuel, or both. Note that ASTM D6732 can be used to measure the level of copper in jet fuel.

9.3 Freezing point information statement for JET A

9.3.1 JET A, with a specification freezing point of -40°C , is not intended for use during extremely cold weather conditions or when the ambient temperature is close to, or below, -40°C . Operational experience shows that aircraft fuel tank temperatures can approach that of the ambient conditions in a time as short as 3 h for a business jet and 6 h for a large transport aircraft. Although lower flying, slower commuter aircraft are not exposed to the same ambient extremes for the same length of time, they could still encounter similar temperatures during flight, particularly if they have loaded cold fuel.

9.3.2 The consequences of low-ambient temperatures are an increase in viscosity and the eventual formation of wax crystals. The increased viscosity could result in adverse changes to the engine fuel regime, whereas an excessive wax accumulation could cause filter blockage, fuel-pump-performance degradation or difficulty with transfer between tanks. Transport Canada has issued guidance and recommendations when operating on JET A fuel in the Airworthiness Notice No. B021 (see 2.2).

9.4 Colour information statement

While this standard does not have a colour requirement, colour may be a useful indicator of fuel quality or contamination. Normally fuel colour ranges from water white (colourless) to a pale straw yellow. Other fuel colours can be the result of crude oil characteristics or refining processes. Darkening of fuel or a change in fuel colour can be the result of product contamination and can indicate that the fuel is off-specification, which could render it unfit and not acceptable for aircraft or engine use, or both. Fuel having various shades of colour, that is, pink, red, green, blue, or a change in colour from the supply source should be investigated to determine the cause of the colour change to ensure suitability for aircraft or engine use, or both.

9.5 Water separation characteristic information statement

The ease of coalescence of water from fuels as influenced by surface-active agents (surfactants) may be assessed by ASTM D7224 or D3948. A high water separation characteristic rating suggests a fuel free of surfactants, whereas a low rating indicates the presence of surfactants. Surfactants can disarm coalescers, thus allowing water to pass through coalescer filters and remain in the fuel. Surfactants can be introduced into the fuel downstream from a refinery distribution system, in storage facilities or deliberately introduced through the addition of specific approved additives. In light of the factors that can degrade water separation characteristics, options such as supplying higher water separation characteristics than the minimum specification should be considered at the point of origin depending upon the means of distribution.

⁴ Hydrogen-processing is any petroleum refining process that uses hydrogen in the presence of a catalyst.

9.6 Refinery processing additive information statement

Additives used in refinery processes, such as corrosion inhibitors, can be carried over in trace quantities into aviation fuel. In a few isolated cases this has resulted in operational problems in aircraft fuel systems. Moreover, the tests and requirements specified in this standard may not be sufficient for detecting trace levels of refinery processing additives. It is therefore recommended that adequate quality assurance and management of change procedures, such as formal risk assessments, be in place to ensure that any relevant refinery processing additive use is well defined and controlled in order to maintain the quality of the finished product.

9.7 Contaminants — Incidental materials — Biodiesel information statement

Biodiesel (Fatty Acid Methyl Esters or FAME) is not an approved component in aviation turbine fuels. The use of FAME in other fuels has raised concern about contamination of aviation turbine fuels, particularly in non-dedicated distribution systems such as multi-product pipelines, marine vessels, railcars and tanker trucks.

The amount of incidental FAME (as defined by ASTM D6751, CAN/CGSB-3.524 or EN 14214) shall not exceed 50 mg/kg. Producers, distributors and users need to take appropriate precautions to avoid contamination. The supplier shall establish the need to test for FAME based on various risk factors that can lead to FAME contamination. Suitable test methods for determining the concentration of FAME in aviation turbine fuels are ASTM D7797/IP 583, IP 585, IP 590 and IP 599. IP 585 shall be the referee method in case of dispute.

Annex A (normative)

Referenced ASTM International publications (see 2.3)

Annual Book of ASTM Standards

- D56 Standard Test Method for Flash Point by Tag Closed Cup Tester
- D86 Standard Test Method for Distillation of Petroleum Products at Atmospheric Pressure
- D130 Standard Test Method for Corrosiveness to Copper from Petroleum Products by Copper Strip Test
- D381 Standard Test Method for Gum Content in Fuels by Jet Evaporation
- D445 Standard Test Method for Kinematic Viscosity of Transparent and Opaque Liquids (and Calculation of Dynamic Viscosity)
- D1298 Standard Test Method for Density, Relative Density (Specific Gravity), or API Gravity of Crude Petroleum and Liquid Petroleum Products by Hydrometer Method
- D1319 Standard Test Method for Hydrocarbon Types in Liquid Petroleum Products by Fluorescent Indicator Adsorption
- D1322 Standard Test Method for Smoke Point of Kerosine and Aviation Turbine Fuel
- D1840 Standard Test Method for Naphthalene Hydrocarbons in Aviation Turbine Fuels by Ultraviolet Spectrophotometry
- D2276 Standard Test Method for Particulate Contaminant in Aviation Fuel by Line Sampling
- D2386 Standard Test Method for Freezing Point of Aviation Fuels
- D2622 Standard Test Method for Sulfur in Petroleum Products by Wavelength Dispersive X-ray Fluorescence Spectrometry
- D2624 Standard Test Methods for Electrical Conductivity of Aviation and Distillate Fuels
- D2887 Standard Test Method for Boiling Range Distribution of Petroleum Fractions by Gas Chromatography
- D3227 Standard Test Method for (Thiol Mercaptan) Sulfur in Gasoline, Kerosine, Aviation Turbine, and Distillate Fuels (Potentiometric Method)
- D3241 Standard Test Method for Thermal Oxidation Stability of Aviation Turbine Fuels (JFTOT Procedure)
- D3242 Standard Test Method for Acidity in Aviation Turbine Fuel
- D3244 Standard Practice for Utilization of Test Data to Determine Conformance with Specifications
- D3338 Standard Test Method for Estimation of Net Heat of Combustion of Aviation Fuels
- D3828 Standard Test Methods for Flash Point by Small Scale Closed Cup Tester
- D3948 Standard Test Method for Determining Water Separation Characteristics of Aviation Turbine Fuels by Portable Separometer

- D4052 Standard Test Method for Density, Relative Density, and API Gravity of Liquids by Digital Density Meter
- D4057 Standard Practice for Manual Sampling of Petroleum and Petroleum Products
- D4171 Standard Specification for Fuel System Icing Inhibitors
- D4177 Standard Practice for Automatic Sampling of Petroleum and Petroleum Products
- D4294 Standard Test Method for Sulfur in Petroleum and Petroleum Products by Energy-Dispersive X-Ray Fluorescence Spectroscopy
- D4529 Standard Test Method for Estimation of Net Heat of Combustion of Aviation Fuels
- D4809 Standard Test Method for Heat of Combustion of Liquid Hydrocarbon Fuels by Bomb Calorimeter (Precision Method)
- D4952 Standard Test Method for Qualitative Analysis for Active Sulfur Species in Fuels and Solvents (Doctor Test)
- D5001 Standard Test Method for Measurement of Lubricity of Aviation Turbine Fuels by the Ball-on-Cylinder Lubricity Evaluator (BOCLE)
- D5006 Standard Test Method for Measurement of Fuel System Icing Inhibitors (Ether Type) in Aviation Fuels
- D5452 Standard Test Method for Particulate Contamination in Aviation Fuels by Laboratory Filtration
- D5453 Standard Test Method for Determination of Total Sulfur in Light Hydrocarbons, Spark Ignition Engine Fuel, Diesel Engine Fuel, and Engine Oil by Ultraviolet Fluorescence
- D5972 Standard Test Method for Freezing Point of Aviation Fuels (Automatic Phase Transition Method)
- D6379 Standard Test Method for Determination of Aromatic Hydrocarbon Types in Aviation Fuels and Petroleum Distillates-High Performance Liquid Chromatography Method with Refractive Index Detection
- D6732 Standard Test Method for Determination of Copper in Jet Fuels by Graphite Furnace Atomic Absorption Spectrometry.
- D6751 Standard Specification for Biodiesel Fuel Blend Stock (B100) for Middle Distillate Fuels
- D7039 Standard Test Method for Sulfur in Gasoline, Diesel Fuel, Jet Fuel, Kerosine, Biodiesel, Biodiesel Blends, and Gasoline-Ethanol Blends by Monochromatic Wavelength Dispersive X-ray Fluorescence Spectrometry
- D7042 Standard Test Method for Dynamic Viscosity and Density of Liquids by Stabinger Viscometer (and the Calculation of Kinematic Viscosity)
- D7224 Standard Test Method for Determining Water Separation Characteristics of Kerosine-Type Aviation Turbine Fuels Containing Additives by Portable Separometer
- D7566 Standard Specification for Aviation Turbine Fuel Containing Synthesized Hydrocarbons
- D7797 Test Method for Determination of the Fatty Acid Methyl Esters Content of Aviation Turbine Fuel Using Flow Analysis by Fourier Transform Infrared Spectroscopy — Rapid Screening Method
- E29 Standard Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications.