Canadian General Standards Board

Office des normes générales du Canada

1-GP-71
Method 30.5
January 1981

(F)1-GP-71
Méthode 30.5
Janvier 1981

WITHDRAWAL

August 1988

CANADIAN GENERAL STANDARDS BOARD

ACCELERATED STABILITY STABILITY AT 40°C

This test method is hereby withdrawn. It has been determined that it is no longer used because the standard that referenced it has been withdrawn.

RETRAIT

Août 1988

OFFICE DES NORMES GÉNÉRALES DU CANADA

STABILITÉ ACCÉLÉRÉE À 40°C

Cette méthode d'essai est retirée par le présent avis. Il a été établi qu'elle n'est plus utilisée dans la mesure où la norme qui s'y référait a également été retirée.

Canada

Canadian General Standards Board

CGSB Ottawa Canada K1A 1G6	Methods of Testing Paints and Pigments	CGSB 1-GP-71
	ACCELERATED STABILITY STABILITY AT 40°C	METHOD 30.5 January 1981

Supersedes Issue of
August 1974

Fill a 250 mL, wide-mouth, colorless, transparent glass bottle provided with a screw cap with aluminum-foil-covered liner, to one-half capacity with the material under test. Place a strip of mild steel (Method 100.1) 20 x 75 mm in the bottle. Tightly seal the bottle and store it 1 month at 40 ± 2°C. At the end of this time examine the material and the steel strip. Then stir the material and re-examine it.

Withdrawn/Retired

Office des normes générales du Canada

ONGC Ottawa Canada K1A 1G6	Méthodes d'essai des peintures et pigments	ONGC (F)1-GP-71
	STABILITÉ ACCÉLÉRÉE À 40°C	MÉTHODE 30.5 Janvier 1981

Remplace l'édition
d'août 1974

Remplir à moitié du produit à l'essai une bouteille de 250 mL en verre transparent, incolore et à large col munie d'un bouchon à vis doublé d'une feuille d'aluminium. Placer dans la bouteille une bande d'acier doux (méthode 100.1) de 20 x 75 mm. Fermer hermétiquement la bouteille et la conserver pendant 1 mois à une température de 40 ± 2°C. Au terme de cette période examiner le produit et la bande d'acier. Remuer le produit et examiner de nouveau.

Withdrawn/Retirée