Canadian General Standards Board

Office des normes générales du Canada

1-GP-71
Method 47.1
August 1974

(F)1-GP-71
Méthode 47.1
Août 1974

WITHDRAWAL

RETRAIT

June 1993

CANADIAN GENERAL STANDARDS BOARD

EFFECT ON STENCIL BRUSHES

With the approval of the CGSB Committee on Paint Test Methods, this test method is hereby withdrawn. It has been determined that it is no longer referenced in any of the CGSB paint standards.

Juin 1993

OFFICE DES NORMES GÉNÉRALES DU CANADA

EFFET SUR LES BROSSES POUR POCHOIR

En accord avec le Comité des méthodes d'essais des peintures, cette méthode d'essai est retirée par le présent avis. Il a été constaté qu'elle n'est plus référencée dans aucune des normes de l'ONGC sur les peintures.

Canada

Canadian General Standards Board

CGSB Ottawa Canada K1A 1G6	Methods of Testing Paints and Pigments	CGSB 1-GP-71
	EFFECT ON STENCIL BRUSHES	METHOD 47.1 August 1974

Supersedes Issue of
December 1958

Withdrawn/Retirée

Wet a stencil brush (22-GP-5) thoroughly with the test sample, and allow the excess to drain off. Lay the brush on its side so that the bristles do not touch an absorbent surface, and allow it to remain for 18 h. Immerse the brush in 1-GP-4 thinner for 15 min, rinse with the thinner, dry and examine.

Office des normes générales du Canada

ONGC Ottawa Canada K1A 1G6	Méthodes d'essai des peintures et pigments	ONGC (F)1-GP-71
	EFFET SUR LES BROSSES POUR POCHOIR	MÉTHODE 47.1 Août 1974

Remplace l'édition
Décembre 1958

Withdrawn/Retirée

Imbiber une brosse pour pochoir (22-GP-5) avec l'échantillon à l'essai et laisser égoutter l'excès. Poser la brosse à plat de telle sorte que la soie ne touche pas à une surface absorbante et la laisser ainsi pendant 18 h. Plonger la brosse dans le diluant 1-GP-4 pendant 15 mn, rincer avec le diluant, sécher et examiner.