Canadian General Standards Board

Office des normes générales du Canada

1-GP-71
Method 108.1
May 1979

(F)1-GP-71
Méthode 108.1
Mai 1979

WITHDRAWAL

June 1989

CANADIAN GENERAL
STANDARDS BOARD

SOLVENT RESISTANCE – MINERAL SPIRITS

This test method is hereby withdrawn. It has been determined that it is no longer used because the standard that referenced it has been withdrawn.

RETRAIT

Juin 1989

OFFICE DES NORMES
GÉNÉRALES DU CANADA

RÉSISTANCE AUX SOLVANTS – ESSENCE MINÉRALE

Cette méthode d'essai est retirée par le présent avis. Il a été établi qu'elle n'est plus utilisée dans la mesure où la norme qui s'y référait a également été retirée.

Canada

Canadian General Standards Board

CGSB Ottawa Canada K1A 1G6	Methods of Testing Paints and Pigments	CGSB 1-GP-71
	SOLVENT RESISTANCE MINERAL SPIRITS	METHOD 108.1 May 1979

Supersedes Issue of
August 1974

Apply (Method 98.2) a coat of the material to steel panels (Method 100.1) and allow to dry 7 d (Method 103.1). Immerse the panels to half their length in 1-GP-4 mineral spirits contained in a covered glass beaker at a temperature of 23 ± 2°C.

At the end of the specified immersion period, remove the panels and examine immediately. Allow the panels to dry for 2 h under standard conditions and examine again.

Withdrawn/Retiree

Office des normes générales du Canada

ONGC Ottawa Canada K1A 1G6	**Méthodes d'essai des peintures et pigments**	**ONGC (F)1-GP-71**
	RÉSISTANCE AUX SOLVANTS **ESSENCE MINÉRALE**	MÉTHODE 108.1 Mai 1979

Remplace l'édition d'août 1974

Appliquer une couche de produit (méthode 98.2) sur des plaques d'acier (méthode 100.1) et laisser sécher pendant 7 d (méthode 103.1). Immerger les plaques, à moitié, dans un bécher de verre couvert contenant de l'essence minérale 1-GP-4, à une température de 23 ± 2°C.

Au terme de la période d'immersion prescrite, retirer les plaques et les examiner immédiatement. Laisser les plaques sécher pendant 2 h dans des conditions normales et les examiner de nouveau

Withdrawn/Retirée