Canadian General Standards Board

Office des normes générales du Canada

1-GP-71
Method 118.6
May 1979

(F)1-GP-71
Méthode 118.6
Mai 1979

WITHDRAWAL

RETRAIT

August 1988

Août 1988

CANADIAN GENERAL STANDARDS BOARD

FLAME RESISTANCE FREE FILM

This test method is hereby withdrawn. It has been determined that it is no longer used because the standard that referenced it has been withdrawn.

OFFICE DES NORMES GÉNÉRALES DU CANADA

RÉSISTANCE À LA COMBUSTION FEUIL DÉTACHÉ

Cette méthode d'essai est retirée par le présent avis. Il a été constaté qu'elle n'est plus utilisée, parce que la norme qui y référait a été retirée.

Canada

Canadian General Standards Board

CGSB Ottawa Canada K1A 1G6	Methods of Testing Paints and Pigments	CGSB 1-GP-71
	FLAME RESISTANCE FREE FILM	METHOD 118.6 May 1979

Supersedes Issue of
August 1974

Adjust the blue flame of a Bunsen burner in a draft-free location so that it is approximately 15 cm high and the inner cone is approximately 7 cm high. Place a specimen 25 mm x 150 mm and 950 ± 65 µm thick, obtained by stripping a panel prepared according to the specification, vertically in the flame so that the lower end of the strip is approximately 4 cm above the inner cone.

Hold the specimen in the flame for 10 s and remove. Note the duration of burning or glowing.

Withdrawn/Retiree

Office des normes générales du Canada

ONGC Ottawa Canada K1A 1G6	Méthodes d'essai des peintures et pigments	ONGC (F)1-GP-71
	RÉSISTANCE À LA COMBUSTION FEUIL DÉTACHÉ	MÉTHODE 118.6 Mai 1979

Remplace l'édition d'août 1974

Dans un endroit sans courant d'air, régler un bec Bunsen pour obtenir une flamme bleue d'environ 15 cm de hauteur dont le cône intérieur aurait environ 7 cm de hauteur. Placer un spécimen de 25 mm x 150 mm et de 950 ± 65 µm d'épaisseur, décollé d'une plaque préparée selon la norme, verticalement au-dessus de la flamme de manière à ce que le bas du feuil soit à environ 4 cm au-dessus du cône.

Faire brûler l'échantillon durant 10 s et l'enlever. Prendre note de la durée de la combustion ou du rougeoiment.

Withdrawn/Retirée