Canadian General Standards Board

Office des normes générales du Canada

1-GP-71
Method 136.2
August 1975

(F)1-GP-71
Méthode 136.2
Août 1975

WITHDRAWAL

RETRAIT

June 1993

Juin 1993

CANADIAN GENERAL STANDARDS BOARD

APPLICATION PROPERTIES — STENCIL INK

With the approval of the CGSB Committee on Paint Test Methods, this test method is hereby withdrawn. It has been determined that it is no longer referenced in any of the CGSB paint standards.

OFFICE DES NORMES GÉNÉRALES DU CANADA

CARACTÉRISTIQUES D'APPLICATION — ENCRE À POCHOIR

En accord avec le Comité des méthodes d'essais des peintures, cette méthode d'essai est retirée par le présent avis. Il a été constaté qu'elle n'est plus référencée dans aucune des normes de l'ONGC sur les peintures.

Canada

Canadian General Standards Board

CGSB Ottawa Canada K1A 1G6	Methods of Testing Paints and Pigments	CGSB 1-GP-71
	APPLICATION PROPERTIES STENCIL INK	METHOD 136.2 August 1975

Supersedes Issue of
August 1974

Withdrawn/Retirée

Apply the ink to the specified panel (Method 97.1 for white pine; Method 101.1 for abraded tinplate) through a sharply cut stencil by means of a 22-GP-5 stencil brush or a fountain brush. Apply only sufficient ink to make legible opaque letters. Lift the stencil straight up and examine the letters. Fill the bristles of the brush with ink and hold the brush vertically for 15 min with the bristles down to determine whether the ink drips.

Office des normes générales du Canada

ONGC Ottawa Canada K1A 1G6	Méthodes d'essai des peintures et pigments	ONGC (F)1-GP-71
	CARACTÉRISTIQUES D'APPLICATION ENCRE À POCHOIR	MÉTHODE 136.2 Août 1975

Remplace l'édition d'août 1974

Appliquer l'encre sur la plaque prescrite (Méthode 97.1) pour le pin blanc et (Méthode 101.1 pour les plaques étamées poncées au moyen d'un pochoir nettement découpé et d'une brosse à réservoir ou d'une brosse à pochoir (F)22-GP-5. Appliquer seulement assez d'encre pour former des lettres opaques et lisibles. Lever carrément le pochoir et examiner les lettres. Imbiber d'encre les poils de la brosse et tenir celle-ci verticalement, poils en bas, pendant 15 min, pour voir si l'encre dégoutte.

Withdrawn/Retirée