Canadian General Standards Board

Office des normes générales du Canada

1-GP-71
Method 137.3
August 1974

(F)1-GP-71
Méthode 137.3
Août 1974

WITHDRAWAL

RETRAIT

June 1993

Juin 1993

CANADIAN GENERAL STANDARDS BOARD

TAPE TEST ON FILMS AFTER IMMERSION

With the approval of the CGSB Committee on Paint Test Methods, this test method is hereby withdrawn. It has been determined that it is no longer referenced in any of the CGSB paint standards.

OFFICE DES NORMES GÉNÉRALES DU CANADA

ESSAI AU RUBAN ADHÉSIF — FEUILS QUI ONT SUBI UNE IMMERSION

En accord avec le Comité des méthodes d'essais des peintures, cette méthode d'essai est retirée par le présent avis. Il a été constaté qu'elle n'est plus référencée dans aucune des normes de l'ONGC sur les peintures.

Canada

Canadian General Standards Board

CGSB Ottawa Canada K1A 1G6	Methods of Testing Paints and Pigments	CGSB 1-GP-71
	TAPE TEST	METHOD 137.3
	ON FILMS AFTER IMMERSION	August 1974

Supersedes Issue of
June 1962

Withdrawn/Retirée

At the end of the specified immersion time remove the panels, wipe dry with a soft cloth, and subject them to the tape test in accordance with Method 137.1.

The complete time lapse from removal of the panel from the water to stripping of the tape shall not exceed 60 s.

Office des normes générales du Canada

ONGC Ottawa Canada K1A 1G6	Méthodes d'essai des peintures et pigments	ONGC (F)1-GP-71
	ESSAI AU RUBAN ADHÉSIF FEUILS QUI ONT SUBI UNE IMMERSION	MÉTHODE 137.3 Août 1974

Remplace l'édition
Juin 1962

Une fois terminée la période d'immersion prescrite, retirer les plaques, les essuyer avec un linge doux et les soumettre à l'essai au ruban spécifié à la méthode 137.1.

Il ne doit pas s'écouler plus de 60 s entre le moment où la plaque est retirée de l'eau et celui où le ruban est décollé de la plaque.

Withdrawn/Retirée