



Government
of Canada

Gouvernement
du Canada

Canadian General
Standards Board Office des normes
générales du Canada

Series 1
Série des 1

WITHDRAWAL

October 2011

Selected standards in the series Paints, pigments and related products

These CGSB standards and National Standards of Canada are hereby withdrawn due to limited use and support for their revision.

The Standards Council of Canada requires that accredited Standards Development Organizations, such as the CGSB, regularly review a consensus Standard to determine whether to re-approve, revise or withdraw. The review cycle is normally five years from the publication date of the latest edition of the Standard.

The information contained in these Standards was originally developed pursuant to a voluntary standards development initiative of the CGSB. The information contained therein may no longer represent the most current, reliable, and/or available information on these subjects. CGSB hereby disclaims any and all claims, representation or warranty of scientific validity, or technical accuracy implied or expressed respecting the information therein contained. The CGSB shall not take responsibility nor be held liable for any errors, omissions, inaccuracies or any other liabilities that may arise from the provision or subsequent use of such information. These Standards are

RETRAIT

Octobre 2011

Sélection de normes de la série Peintures, pigments et produits connexes

Ces normes de l'ONGC et ces Normes nationales du Canada sont retirées par le présent avis en raison de leur utilisation limitée et du manque de support pour leur révision.

Le Conseil canadien des normes exige que les organismes accrédités d'élaboration de normes, tel que l'ONGC, effectue régulièrement un examen des normes consensuelles afin de déterminer s'il y a lieu d'en renouveler l'approbation, de les réviser ou de les retirer. Le cycle d'examen d'une norme est généralement de cinq ans à partir de la date de publication de la dernière édition de celle-ci.

L'information contenue dans ces normes a été élaborée initialement en vertu d'une initiative volontaire d'élaboration de normes de l'ONGC. Elle peut ne plus représenter l'information disponible et/ou l'information la plus actuelle ou la plus fiable à ce sujet. L'ONGC décline par la présente toute responsabilité à l'égard de toute affirmation, déclaration ou garantie de validité scientifique ou d'exactitude technique implicite ou explicite relative à l'information contenue dans ces normes. L'ONGC n'assumera aucune responsabilité et ne sera pas tenu responsable quant à toute erreur, omission, inexactitude ou autre conséquence pouvant découler de la fourniture ou de l'utilisation subséquente de

Canada

Experience and excellence

Expérience et excellence

CGSB
ONGC

to be referred to for archival purposes only as their content has been repealed as of the date on this withdrawal notice.

Archived copies of withdrawn standards for historic or archival purposes are still available from the CGSB Sales Centre by telephone at 819-956-0425 or 1-800-665-2472, by fax at 819-956-5740, by Internet at www.tpsgc-pwgsc.gc.ca/ongc-cgsb/, by e-mail at ncr.CGSB-ONGC@tpsgc-pwgsc.gc.ca or by mail at Sales Centre, Canadian General Standards Board, 11 Laurier Street, Gatineau, Canada K1A 1G6.

CAN/CGSB-1.5-M91

Low Flash Petroleum Spirits Thinner
(ICS 87.040)

CAN/CGSB-1.28-98

Exterior Alkyd House Paint (ICS 87.040)

CAN/CGSB-1.36-97

General Purpose Interior Alkyd Varnish
(ICS 87.040)

CAN/CGSB-1.38-2000

Interior Enamel Undercoater (ICS 87.040)

CAN/CGSB-1.40-97

Anticorrosive Structural Steel Alkyd Primer
(ICS 87.040)

CAN/CGSB-1.57-2003

Interior Alkyd Semigloss Enamel
(ICS 87.040)

CAN/CGSB-1.59-97

Alkyd Exterior Gloss Enamel (ICS 87.040)

CAN/CGSB-1.60-97

Interior Alkyd Gloss Enamel (ICS 87.040)

cette information. Ces normes doivent être consultées à des fins archivistiques seulement puisque leur contenu a été révoqué à la date du présent avis de retrait.

Des copies archivées des normes retirées peuvent être obtenues à des fins historiques ou archivistiques auprès du Centre des ventes de l'ONGC. Il suffit d'en faire la demande par téléphone au 819-956-0425 ou 1-800-665-2472, par télécopieur au 819-956-5740, par Internet à : www.tpsgc-pwgsc.gc.ca/ongc-cgsb/, par courriel à ncr.CGSB-ONGC@tpsgc-pwgsc.gc.ca, ou par courrier adressé au Centre des ventes, Office des normes générales du Canada, 11, rue Laurier, Gatineau, Canada K1A 1G6.

CAN/CGSB-1.5-M91

Diluant, essence minérale à faible point d'éclair (ICS 87.040)

CAN/CGSB-1.28-98

Peinture aux résines alkydes d'extérieur pour bâtiments (ICS 87.040)

CAN/CGSB-1.36-97

Vernis d'intérieur aux résines alkydes d'usage général (ICS 87.040)

CAN/CGSB-1.38-2000

Peinture-émail d'intérieur, pour couche de fond (ICS 87.040)

CAN/CGSB-1.40-97

Peinture pour couche primaire anticorrosion, aux résines alkydes, pour acier de construction (ICS 87.040)

CAN/CGSB-1.57-2003

Peinture-émail, d'intérieur, semi-brillante, aux résines alkydes (ICS 87.040)

CAN/CGSB-1.59-97

Peinture-émail, d'extérieur, brillante, aux résines alkydes (ICS 87.040)

CAN/CGSB-1.60-97

Peinture-émail brillante d'intérieur aux résines alkydes (ICS 87.040)

CAN/CGSB-1.61-2004

Exterior and Interior Marine Alkyd Enamel
(ICS 87.040)

CAN/CGSB-1.69-98

Aluminum Paint (ICS 87.040)

1-GP-71 (Oct 1983)

Methods of Testing Paints and Pigments
(ICS 87.040)

1-GP-71

Methods of Testing Paints and Pigments

No. 5-96

Drying Times of Paints and Related
Coatings (ICS 87.040)

No. 38-96

Blushing Resistance of Lacquer
Finishes (ICS 87.040)

No. 73-96

Beilstein Test for Chlorinated Solvents
(ICS 87.040)

CAN/CGSB-1.73-97

Exterior and Interior Enamel for Floors
(ICS 87.040)

CAN/CGSB-1.74-2001

Alkyd Traffic Paint (ICS 87.040)

CAN/CGSB-1.76-2000

Interior and Exterior Heat-Resistant Enamel
(ICS 87.040)

CAN/CGSB-1.81-M90

Air Drying and Baking Alkyd Primer for
Vehicles and Equipment (ICS 87.040)

CAN/CGSB-1.84-M91

Alkyd Primer for Hardwood (ICS 87.040)

CAN/CGSB-1.61-2004

Peinture-émail aux résines alkydes,
d'extérieur et d'intérieur, marine
(ICS 87.040)

CAN/CGSB-1.69-98

Peinture à l'aluminium (ICS 87.040)

1-GP-71 (oct. 1983)

Méthodes d'essai des peintures et pigments
(ICS 87.040)

1-GP-71

Méthodes d'essai des peintures et pigments

N° 5-96

Durée de séchage des peintures et
revêtements apparentés (ICS 87.040)

N° 38-96

Résistance à l'opalescence des
produits-laque de finition (ICS 87.040)

N° 73-96

Détermination de la présence de
solvants chlorés par l'essai de Beilstein
(ICS 87.040)

CAN/CGSB-1.73-97

Peinture-émail d'extérieur et d'intérieur,
pour sols (ICS 87.040)

CAN/CGSB-1.74-2001

Peinture alkyde de démarcation routière
(ICS 87.040)

CAN/CGSB-1.76-2000

Peinture-émail résistant à la chaleur,
d'intérieur et d'extérieur (ICS 87.040)

CAN/CGSB-1.81-M90

Peinture pour couche primaire aux résines
alkydes, séchant à l'air ambiant et au four,
pour véhicules automobiles et équipement
(ICS 87.040)

CAN/CGSB-1.84-M91

Peinture d'impression aux résines alkydes,
pour bois dur (ICS 87.040)

CAN/CGSB-1.88-92

Gloss Alkyd Enamel, Air Drying and Baking
(ICS 87.040)

CAN/CGSB-1.100-99

Interior Flat Latex Paint (ICS 87.040)

CAN/CGSB-1.104-M91

Semigloss Alkyd Air Drying and Baking
Enamel (ICS 87.040)

CAN/CGSB-1.105-M91

Quick-Drying Primer (ICS 87.040)

CAN/CGSB-1.114-M91

Quick-Drying Flat Enamel (ICS 87.040)

CAN/CGSB-1.118-95

Interior Flat Alkyd Finish (ICS 87.040)

CAN/CGSB-1.119-2000

Interior Latex Primer-Sealer (ICS 87.040)

CAN/CGSB-1.122-99

Anticorrosive Vinyl Primer (ICS 87.040)

CAN/CGSB-1.132-M90

Zinc Chromate Primer, Low Moisture
Sensitivity (ICS 87.040)

CAN/CGSB-1.135-99

Flat Alkyd Enamel for Equipment
(ICS 87.040)

CAN/CGSB-1.138-97

Exterior Latex Flat Paint (ICS 87.040)

CAN/CGSB-1.143-98

Silicone Alkyd Heat-Resistant Aluminum
Enamel (ICS 87.040)

CAN/CGSB-1.88-92

Peinture-émail brillante aux résines alkydes,
séchant à l'air ambiant et au four
(ICS 87.040)

CAN/CGSB-1.100-99

Peinture-émulsion mate d'intérieur
(ICS 87.040)

CAN/CGSB-1.104-M91

Peinture-émail semi-brillante aux résines
alkydes séchant à l'air ambiant et au four
(ICS 87.040)

CAN/CGSB-1.105-M91

Peinture pour couche primaire à séchage
rapide (ICS 87.040)

CAN/CGSB-1.114-M91

Peinture-émail mate à séchage rapide
(ICS 87.040)

CAN/CGSB-1.118-95

Peinture de finition mate d'intérieur aux
résines alkydes (ICS 87.040)

CAN/CGSB-1.119-2000

Peinture-émulsion d'impression d'intérieur
(ICS 87.040)

CAN/CGSB-1.122-99

Peinture pour couche primaire, aux résines
vinyliques, anticorrosion (ICS 87.040)

CAN/CGSB-1.132-M90

Peinture pour couche primaire, au chromate
de zinc, à faible sensibilité à l'humidité
(ICS 87.040)

CAN/CGSB-1.135-99

Peinture-émail mate aux résines alkydes
pour équipement (ICS 87.040)

CAN/CGSB-1.138-97

Peinture-émulsion (latex) mate, d'extérieur
(ICS 87.040)

CAN/CGSB-1.143-98

Peinture-émail aux résines silicones-
alkydes résistante à la chaleur (ICS 87.040)

CAN/CGSB-1.145-97

Solvent-Based Pigmented Stain
(ICS 87.040)

CAN/CGSB-1.146-99

Cold Curing, Gloss Epoxy Coating
(ICS 87.040)

CAN/CGSB-1.150-M91

Clear Lacquer for Wood Furniture
(ICS 87.040)

CAN/CGSB-1.153-2000

High-Build, Gloss Epoxy Coating
(ICS 87.040)

CAN/CGSB-1.154-M89

Latex Type Paint for Concrete Floors
(ICS 87.040)

CAN/CGSB-1.158-M89

Cellulose Nitrate Primer, Modified Alkyd
Type (ICS 87.040)

CAN/CGSB-1.159-92

Acrylic Cellulose Nitrate Gloss Lacquer
(ICS 87.040)

CAN/CGSB-1.160-93

Low Gloss Acrylic Cellulose Nitrate
Lacquer (ICS 87.040)

CAN/CGSB-1.162-2004

Emulsion Coating for Stucco and Masonry
(ICS 87.040)

CAN/CGSB-1.165-2004

Cold-Curing Epoxy Primer (ICS 87.040)

CAN/CGSB-1.171-98

Inorganic Zinc Coating (ICS 87.040)

CAN/CGSB-1.175-97

Polyurethane Interior Coating (ICS 87.040)

CAN/CGSB-1.145-97

Teinture pigmentée à base de solvant
(ICS 87.040)

CAN/CGSB-1.146-99

Revêtement aux résines époxydiques,
durcissant à froid, brillant (ICS 87.040)

CAN/CGSB-1.150-M91

Vernis-laque pour meubles en bois
(ICS 87.040)

CAN/CGSB-1.153-2000

Revêtement par peinture aux résines
époxydiques, à pouvoir garnissant élevé,
brillant (ICS 87.040)

CAN/CGSB-1.154-M89

Peinture-émulsion (latex) pour sols en béton
(ICS 87.040)

CAN/CGSB-1.158-M89

Peinture-laque pour couche primaire, au
nitrate de cellulose et aux résines alkydes
modifiées (ICS 87.040)

CAN/CGSB-1.159-92

Produit-laque brillant à la résine acrylique et
au nitrate de cellulose (ICS 87.040)

CAN/CGSB-1.160-93

Peinture-laque aux résines acryliques et au
nitrate de cellulose, peu brillante
(ICS 87.040)

CAN/CGSB-1.162-2004

Revêtement de type émulsion pour stuc et
maçonnerie (ICS 87.040)

CAN/CGSB-1.165-2004

Peinture pour couche primaire aux résines
époxydiques, durcissant à froid
(ICS 87.040)

CAN/CGSB-1.171-98

Enduit au zinc minéral (ICS 87.040)

CAN/CGSB-1.175-97

Revêtement de polyuréthane d'intérieur
(ICS 87.040)

CAN/CGSB-1.176-2000

Interior Clear Moisture-Curing Polyurethane Coating (ICS 87.040)

CAN/CGSB-1.177-M91

Two-Component Polyurethane Coating, Resistant to Chalking and Yellowing (ICS 87.040)

1-GP-180Ma (Feb 1996)

Coating, Polyurethane, Two-Package, General Purpose (ICS 87.040)

CAN/CGSB-1.181-99

Ready-Mixed Organic Zinc-Rich Coating (ICS 87.040)

CAN/CGSB-1.183-99

Zinc-Rich Epoxy Coating (ICS 87.040)

CAN/CGSB-1.184-98

Coal Tar-Epoxy Coating (ICS 87.040)

CAN/CGSB-1.188-2004

Emulsion Filler for Masonry Block (ICS 87.040)

CAN/CGSB-1.189-2000

Exterior Alkyd Primer for Wood (ICS 87.040)

CAN/CGSB-1.190-M90

Sanding Type Primer Surfacer (ICS 87.040)

1-GP-191M (Apr 1980)

Enamel, Automotive Refinishing, Fast Drying, Gloss (ICS 87.040)

1-GP-192Ma (Feb 1985)

Deck Coating, Nonslip, Epoxy (ICS 87.040)

CAN/CGSB-1.176-2000

Revêtement de polyuréthane, d'intérieur, durci à l'humidité, non pigmenté (ICS 87.040)

CAN/CGSB-1.177-M91

Revêtement de polyuréthane, à deux constituants séparés, non jaunissant et non farinant (ICS 87.040)

1-GP-180Ma (févr. 1996)

Revêtement de polyuréthane, à deux constituants séparés, pour utilisation générale (ICS 87.040)

CAN/CGSB-1.181-99

Enduit riche en zinc, organique et préparé (ICS 87.040)

CAN/CGSB-1.183-99

Enduit aux résines époxydiques, riche en zinc (ICS 87.040)

CAN/CGSB-1.184-98

Revêtement à base de goudron de houille-résines époxydiques (ICS 87.040)

CAN/CGSB-1.188-2004

Apprêt-émulsion pour blocs de maçonnerie (ICS 87.040)

CAN/CGSB-1.189-2000

Peinture d'impression, d'extérieur, aux résines alkydes, pour le bois (ICS 87.040)

CAN/CGSB-1.190-M90

Peinture pour couche primaire surfaçante de type ponçable (ICS 87.040)

1-GP-191M (avr. 1980)

Peinture-émail brillante, à séchage rapide, pour le repeinture des carrosseries de véhicules automobiles (ICS 87.040)

1-GP-192Ma (févr. 1985)

Revêtement de pont, antidérapant, aux résines époxydiques (ICS 87.040)

CAN/CGSB-1.193-99

High-Build Epoxy Marine Coating
(ICS 87.040)

CAN/CGSB-1.195-99

Interior Latex Semigloss Paint (ICS 87.040)

CAN/CGSB-1.198-2001

Cementitious Primer for Galvanized
Surfaces (ICS 87.040)

1-GP-200Ma (Jan 1985)

Deck Coating, Nonslip, Polyurethane
(ICS 87.040)

CAN/CGSB-1.202-2003

Interior Alkyd Low Gloss Enamel
(ICS 87.040)

CAN/CGSB-1.203-2003

Exterior Latex Wood Primer (ICS 87.040)

CAN/CGSB-1.204-98

Exterior Latex Pigmented Stain
(ICS 87.040)

CAN/CGSB-1.205-2003

Sealer for Application to Asbestos-Fibre
Releasing Materials (ICS 87.040)

CAN/CGSB-1.207-98

Low-Temperature Curing Epoxy Coating
(ICS 87.040)

CAN/CGSB-1.208-99

Marine Interior Water-Borne Gloss Enamel
(ICS 87.040)

CAN/CGSB-1.209-2003

Interior Latex Low Gloss Paint (ICS 87.040)

CAN/CGSB-1.210-2003

Quick-Drying Alkyd Primer for Structural
Steel (ICS 87.040)

CAN/CGSB-1.193-99

Revêtement aux résines époxydiques, à
pouvoir garnissant élevé, marin
(ICS 87.040)

CAN/CGSB-1.195-99

Peinture-émulsion semi-brillante d'intérieur
(ICS 87.040)

CAN/CGSB-1.198-2001

Peinture primaire additionnée de ciment,
pour surfaces galvanisées (ICS 87.040)

1-GP-200Ma (janv. 1985)

Revêtement de pont, antidérapant, aux
résines polyuréthannes (ICS 87.040)

CAN/CGSB-1.202-2003

Peinture-émail d'intérieur, aux résines
alkydes, peu brillante (ICS 87.040)

CAN/CGSB-1.203-2003

Peinture-émulsion (latex) d'impression
extérieure, pour bois (ICS 87.040)

CAN/CGSB-1.204-98

Teinture-émulsion pigmentée pour extérieur
(ICS 87.040)

CAN/CGSB-1.205-2003

Peinture d'obturation pour matériaux
renfermant des fibres d'amianté
(ICS 87.040)

CAN/CGSB-1.207-98

Revêtement aux résines époxydiques
durcissant à basse température
(ICS 87.040)

CAN/CGSB-1.208-99

Peinture-émail brillante en suspension
aqueuse, marine, d'intérieur (ICS 87.040)

CAN/CGSB-1.209-2003

Peinture-émulsion d'intérieur peu brillante
(ICS 87.040)

CAN/CGSB-1.210-2003

Peinture primaire aux résines alkydes à
séchage rapide pour acier de charpente
(ICS 87.040)

CAN/CGSB-1.211-95

Coating Systems for Marine Floating Navigational Aids (Buoys) (ICS 87.040)

CAN/CGSB-1.212-2004

Heavy-Metal-Free Marine Primer for Steel and Light-Alloy Surfaces (ICS 87.040)

CAN/CGSB-1.213-2004

Etch Primer (Pretreatment Coating or Tie Coat) for Steel and Aluminum (ICS 87.040)

CAN/CGSB-1.214-2004

Heavy-Metal-Free, Water-Borne, Marine Primer for Steel and Light-Alloy Surfaces (ICS 87.040)

CAN/CGSB-1.215-96

Two-Package Epoxy Blockfiller (ICS 87.040)

CAN/CGSB-1.216-97

Exterior Water-Borne Gloss Enamel (ICS 87.040)

CAN/CGSB-1.219-2001

Lead and Chromate-Free Waterborne Traffic Paint (ICS 87.040)

CAN/CGSB-1.220-2001

Lead and Chromate-Free Alkyd Traffic Paint (ICS 87.040)

CAN/CGSB-1.223-2004

Heavy-Metal-Free, Water-Borne Wash Primer-Tie Coat (ICS 87.040)

CAN/CGSB-1.300-2000

Applied Coating System of Semigloss Baked Finish for Metal Office Furniture (ICS 87.040)

CAN/CGSB-1.500-75

Methods for Test for Toxic Trace Elements in Protective Coatings (ICS 87.040)

CAN/CGSB-1.211-95

Systèmes de revêtement pour aides à la navigation flottantes (bouées) (ICS 87.040)

CAN/CGSB-1.212-2004

Peinture primaire sans métal lourd, marine, pour surfaces en acier et en alliage léger (ICS 87.040)

CAN/CGSB-1.213-2004

Peinture primaire réactive (enduit de traitement préliminaire ou couche de liaison) pour l'acier et l'aluminium (ICS 87.040)

CAN/CGSB-1.214-2004

Peinture primaire, sans métal lourd, en suspension aqueuse, marine, pour surfaces en acier et en alliage léger (ICS 87.040)

CAN/CGSB-1.215-96

Apprêt pour blocs aux résines époxydiques en deux constituants (ICS 87.040)

CAN/CGSB-1.216-97

Peinture-émail brillante d'extérieur en suspension aqueuse (ICS 87.040)

CAN/CGSB-1.219-2001

Peinture à l'eau de démarcation routière sans plomb ni chromate (ICS 87.040)

CAN/CGSB-1.220-2001

Peinture alkyde de démarcation routière sans plomb ni chromate (ICS 87.040)

CAN/CGSB-1.223-2004

Peinture primaire réactive – Couche de liaison, sans métal lourd, en suspension aqueuse (ICS 87.040)

CAN/CGSB-1.300-2000

Système de revêtement de finition semi-brillant, cuit au four, pour meubles métalliques de bureau (ICS 87.040)

CAN/CGSB-1.500-75

Méthodes d'essai des éléments toxiques à l'état de trace dans les revêtements protecteurs (ICS 87.040)

CAN/CGSB-1.501-M89

Method for Permeance of Coated
Wallboard (ICS 87.040)

CAN/CGSB-1.501-M89

Méthode de détermination de la perméance
des panneaux muraux revêtus (ICS 87.040)

NATIONAL STANDARD OF CANADA

CAN/CGSB-1.84-M91

Supersedes 1-GP-84M

Alkyd Primer For Hardwood



QUALITY

Withdrawn/Retiré

Canadian General Standards Board

CGSB

The CANADIAN GENERAL STANDARDS BOARD (CGSB), under whose auspices this standard has been developed is a government agency within the Federal Department of Supply and Services. CGSB is engaged in the production of voluntary standards in a wide range of subject areas through the media of standards committees and the consensus process. The standards committees are composed of representatives of relevant interests including producers, consumers and other users, retailers, governments, educational institutions, technical, professional and trade societies, and research and testing organizations. Any given standard is developed on the consensus of views expressed by such representatives. The Minister's Advisory Council on CGSB reviews the results of the consensus process.

CGSB has been accredited by the Standards Council of Canada as a national standards-writing organization. The standards that it develops and offers as National Standards of Canada conform to the criteria and procedures established for this purpose by the Standards Council of Canada. In addition to standards it publishes as national standards, CGSB produces standards to meet particular needs, in response to requests from a variety of sources in both the public and private sectors. Both CGSB standards and national standards developed by CGSB are developed in conformance with the policies described in the Policy Manual for the Development and Maintenance of Standards by CGSB.

CGSB standards are subject to review and revision at any time, so as to ensure that they keep abreast of technological progress. Suggestions for their improvement, which are always welcome, should be brought to the notice of the standards committees concerned. Changes to standards are issued either as separate amendment sheets or in new editions of standards.

An up-to-date listing of CGSB standards, including details on latest issues and amendments, and ordering instructions, will be found in the CGSB Catalogue, which is published annually and is available without charge upon request.

Although the intended primary application of this standard is stated in its Scope, it is important to note that it remains the responsibility of the users of the standard to judge its suitability for their particular purpose.

Many tests required by CGSB standards are inherently hazardous. CGSB neither assumes nor accepts any responsibility for any injury or damage that may occur during or as the result of tests, wherever performed.

CGSB takes no position respecting the validity of any patent rights asserted with any item connected with this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights are entirely their own responsibility.

Further information on CGSB and its services and standards may be obtained from:

The Secretary
Canadian General Standards Board
Ottawa, Canada
K1A 1G6

The STANDARDS COUNCIL OF CANADA is the coordinating body of the National Standards System, a federation of independent, autonomous organizations working towards the further development and improvement of voluntary standardization in the national interest.

The principal objectives of the Council are to foster and promote voluntary standardization as a means of advancing the national economy, benefiting the health, safety and welfare of the public, assisting and protecting the consumer, facilitating domestic and international trade, and furthering international co-operation in the field of standards.

A National Standard of Canada is a standard which has been approved by the Standards Council of Canada and one which reflects a reasonable agreement among the views of a number of capable individuals whose collective interests provide, to the greatest practicable extent, a balance of representation of producers, users, consumers and others with relevant interests, as may be appropriate to the subject in hand. It normally is a standard that is capable of making a significant and timely contribution to the national interest.

Approval of a standard as a National Standard of Canada indicates that a standard conforms to the criteria and procedures established by the Standards Council of Canada. Approval does not refer to the technical content of the standard; this remains the continuing responsibility of the accredited standards-writing organization.

Those who have a need to apply standards are encouraged to use National Standards of Canada whenever practicable. These standards are subject to periodic review; therefore, users are cautioned to obtain the latest edition from the organization preparing the standard.

The responsibility for approving National Standards of Canada rests with the:

Standards Council of Canada
350 Sparks Street
Ottawa, Ontario
K1P 6N7

How to order CGSB Publications:

- by Telephone — (819) 956-0425 or
— (819) 956-0426
- by Fax — (819) 956-5644
- by Mail — CGSB, Sales Unit
Ottawa, Canada
K1A 1G6
- in Person — Place du Portage III, 9C1
11 Laurier Street
Hull, Quebec

ALKYD PRIMER FOR HARDWOOD

This new edition supersedes 1-GP-84M, September 1983. There are no substantial technical changes.

The Department of National Defence administers a Qualification Listing Program for products conforming to the requirements of this standard. Further information on the listing program is available from the Director of Engineering and Maintenance Planning and Standardization (DEMPS 4) Ottawa, Canada K1A 0K2.

Prepared by the

Canadian General Standards Board **CGSB**

Approved by the

Standards Council of Canada



Published May 1991 by the
Canadian General Standards Board
Ottawa, Canada K1A 1G6

©Minister of Supply and Services Canada — 1991

No part of this publication may be reproduced in any form without the prior permission of the publisher.

CANADIAN GENERAL STANDARDS BOARD
COMMITTEE ON AERONAUTICAL AND INDUSTRIAL
PAINT FINISHES

(Membership at date of approval)

Afzal, A. <i>Chairman</i>	Department of National Defence
Abel, B.	Reichhold Chemicals Ltd.
Ashton, H.E.	National Research Council of Canada
Benner, H.J.	Lanark Coating Services Ltd.
Carlyle, A.G.	Department of National Defence
Cerullo, N.G.	Department of National Defence
Corbeil, G.	Sico Paint Inc.
Croutch, V.	ORTECH International
Desbiens, Y.	Canadian Arsenals Ltd.
Gonsalves, I.	Glidden Company (Canada) Ltd.
Hebdige, B.A.	International Paints (Canada) Ltd.
Johnston, D.J.	Tristar Coatings
King, W.B.G.	The Standards Manufacturing Co. Ltd.
Kulkarni, V.	PPG Industries Canada Inc.
Pfaff, T.A.	Valspar Inc.
Sharma, V.	Denault Paint Ltd.
Shillum, B.	Tristar Coatings
Taada, K.	Department of Supply and Services
Tong, P.	Union Carbide du Canada Ltd.
Viens, P.	Quebec Hydro
Wiezoreck, G.	West Coast Painting Co. Ltd.
Khan, R.A. <i>Secretary</i>	Canadian General Standards Board

Acknowledgement is made for the French translation of this National Standard of Canada by the Translation Bureau of the Department of the Secretary of State and for the publishing by MGL Publishing Inc.

CANADIAN GENERAL STANDARDS BOARD
ALKYD PRIMER FOR HARDWOOD

1. SCOPE

- 1.1 This standard applies to grey alkyd-base primer suitable for use under enamels on exterior wood such as wood components of motor vehicles and equipment.
- 1.2 For more detailed information on intended uses see par. 7.2.
- 1.3 The testing and evaluation of a product against this standard may require the use of materials and/or equipment that could be hazardous. This document does not purport to address all the safety aspects associated with its use. Anyone using this standard has the responsibility to consult the appropriate authorities and to establish appropriate health and safety practices in conjunction with any existing applicable regulatory requirements prior to its use.

2. APPLICABLE PUBLICATIONS

- 2.1 The following publications are applicable to this standard:

2.1.1 Canadian General Standards Board (CGSB)

1-GP-12— Standard Paint Colors, Part III
1-GP-70M— Thinner, High Solvency
1-GP-71— Methods of Testing Paints and Pigments
1-GP-88M— Gloss Alkyd Enamel, Air Drying and Baking
1-GP-93M— Paint, Aluminum, Marine
1-GP-99M— Varnish, Phenolic Resin, Exterior and Marine
1-GP-102M— Clear, Alkyd Type Sealer.

2.1.2 Department of Consumer and Corporate Affairs

Hazardous Products Act.

2.1.3 ASTM

D 1210 — Test Method for Fineness of Dispersion of Pigment-Vehicle Systems.

- 2.2 Reference to the publications in par. 2.1.1 and 2.1.3 and other related standards is to the latest issues unless otherwise specified by the authority applying this standard. The sources for all publications are shown in the Notes section.

3. GENERAL REQUIREMENTS

- 3.1 The primer shall consist of suitable pigments adequately dispersed in a medium-length alkyd vehicle together with the necessary thinners and driers.
- 3.2 The primer as supplied shall be suitable for application by brush and shall be satisfactory for spraying or dipping when reduced according to the manufacturer's instructions, with thinner conforming to CGSB standard 1-GP-70M.
- 3.3 The dried film of the primer applied by brushing, dipping or spraying shall have a smooth, hard, uniform, matt or low-gloss finish, free from wrinkling and sagging.

- 3.4 The primer shall not skin, thicken excessively nor cake in the original unopened container for one year from date of shipment when stored at temperatures not exceeding 40°C. At the end of this time, it shall be capable of being readily mixed to a uniform condition by stirring and shall meet the requirement for drying time (par. 4.2).

4. DETAILED REQUIREMENTS

Primer to this standard shall comply with the following detailed requirements when tested in accordance with the specified test methods:

		Test Method			
		Min.	Max.	CGSB 1-GP-71	ASTM
4.1	Consistency, Krebs units	65	85	4.5	—
4.2	Drying time	—	—	5.1	—
4.2.1	Set to touch, h	—	2	—	—
4.2.2	Dry hard, h	—	6	—	—
4.3	Fineness of grind, Hegman	5	—	—	D 1210
4.4	60° gloss, units	—	30	13.1	—
4.5	Hiding power, m ² /L	12	—	14.1	—
4.6	Volatile matter, % by mass	—	35	17.1	—
4.7	Nonvolatile vehicle, % by mass	20	30	19.1	—
4.8	Phthalic anhydride, % by mass of nonvolatile vehicle	30	—	57.1	—
4.9	Rosin and rosin derivatives, % of NVV	—	3.0	60.2	—
4.10	Colour — The colour of the primer shall not be lighter than CGSB standard 1-GP-12 Grey 501-308 nor darker than Grey 501-310 when tested in accordance with CGSB standard 1-GP-71, Method 12.9.				
4.11	Skinning Properties — The primer shall be nonskinning when tested in accordance with CGSB standard 1-GP-71, Method 10.1.				
4.12	Pigment Composition — Calcium compounds soluble in diluted acid shall not exceed the equivalent of 10.0% calcium oxide (CaO) by mass of the dry pigment when tested in accordance with CGSB standard 1-GP-71, Method 50.15.				
4.13	Water Resistance — A film of primer, immersed 18 h in water at 23°C, shall show no blistering, peeling, wrinkling or lifting. After subsequent drying for 2 h it shall show no softening, whitening, dulling or other defects when tested in accordance with CGSB standard 1-GP-71, Method 110.1.				
4.14	Scratch Resistance — The dried film shall withstand the scratch test under a load of 500 g without exposing the metal through the scratch in the film when tested in accordance with CGSB standard 1-GP-71, Method 116.2.				
4.15	Flexibility — The dried primer film, after accelerated aging, shall show no cracking when subjected to the bending test at 23°C using a 3.2 mm diameter mandrel, in accordance with CGSB standard 1-GP-71, Method 119.1.				

- 4.16 **Sanding Properties** — A film of the primer, dried 18 h, shall be smooth and in suitable condition to receive a coat of enamel conforming to CGSB standard 1-GP-88M Type 1 after thirty strokes of No. 360 abrasive paper, and shall not cause clogging or gumming of the paper. The enamel, over the abraded portion of the film, shall have no defects such as the loss of gloss and scratch marks due to poor sanding properties of the primer when tested in accordance with CGSB standard 1-GP-71, Method 127.1.
- 4.17 **Behaviour Toward Topcoats** — When subjected to the enamel holdout test using enamel conforming to CGSB standard 1-GP-88M Type 1 as a topcoat, the finish shall be uniform in appearance with no wrinkling and shall have a gloss of not less than 80 units when tested in accordance with CGSB standard 1-GP-71, Method 130.3.
- 4.18 **Accelerated Weathering Resistance** — A finish system of the primer under test, topcoated with enamel conforming to CGSB standard 1-GP-88M Type 1, shall withstand fifteen 24 h cycles in a twin-arc accelerated weathering machine without showing any blistering, checking, cracking, flaking or appreciable loss of gloss when tested in accordance with the procedures in par. 6.3.

5. PREPARATION FOR DELIVERY

- 5.1 Unless otherwise specified, (par. 7.1), preparation for delivery shall conform to normal commercial practice.
- 5.2 **Labelling** — In addition to complying with the labelling requirements of any relevant Acts or Regulations, each container shall be suitably labelled to show the following information:

Name of material

Standard number: CAN/CGSB-1.84-M91

Colour and number, CGSB 1-GP-12

Manufacturer's name and address

Manufacturer's batch number

Manufacturer's code number

Date of manufacture

Thinning instructions for spraying and for dipping using thinner conforming to CGSB standard 1-GP-70M.

- 5.3 **Toxic Elements** — This material shall be labelled to conform to the requirements of the Hazardous Products Act in respect to designated toxic elements.

6. INSPECTION

- 6.1 **Sampling** — Sampling shall be carried out in accordance with CGSB standard 1-GP-71, Method 1.1.
- 6.2 **Testing**
- 6.2.1 When test panels are prepared by spraying, the amount of thinner conforming to CGSB standard 1-GP-70M used to reduce the primer shall be in accordance with the manufacturer's instructions.
- 6.3 **Accelerated Weathering Resistance** — Select and prepare birch panels 150 x 70 x 10 mm as described in CGSB standard 1-GP-71, Method 97.1 (except, do not seal the ends with CGSB 1-GP-99M varnish). Immerse the panels in clear alkyd-type sealer conforming to CGSB standard 1-GP-102M for 3 min, remove, drain and allow to dry 18 h (Method 103.1) in a vertical position. Apply (Method 98.2) a coat of the primer under test and allow to dry 24 h. Apply one coat of enamel conforming to CGSB standard 1-GP-88M, Type 1 and condition 7 d (Method 103.1), then coat the backs and edges of the panels with aluminum paint conforming to CGSB standard 1-GP-93M. Expose and examine the panels in accordance with CGSB standard 1-GP-71 Methods 122.1 and 122.2.

7. NOTES

- 7.1 **Options** — The following option must be specified in the application of this standard:
- a. Preparation for delivery, if other than as specified (par. 5.1).

7.2 Intended Uses

- 7.2.1 Primer complying with this standard is for use under enamels on wood surfaces of motor vehicles and equipment. It is not intended for use on metals or as a primer for house paint.
- 7.2.2 Although it may be applied by brush, the primer is usually applied by spray. A sealer is not essential except on porous wood, but when one is considered necessary, a sealer conforming to CGSB standard 1-GP-102M is recommended. Open-grain wood should be filled with filler in accordance with the manufacturer's instructions. The primer is intended to be topcoated with gloss enamel conforming to CGSB standard 1-GP-88M. It may also be topcoated with exterior enamels conforming to CGSB standard 1-GP-59M or 1-GP-104M.
- 7.2.3 For a description and uses of other coatings and related materials covered by CGSB standards, see CGSB standard 1-GP-72, Guide to the Selection of Paint Standards on Use Basis.

7.3 Related Publication (as to use)

CGSB standard 1-GP-189M — Primer Alkyd, Wood, Exterior.

7.4 Sources of Referenced Publications

- 7.4.1 The publications referred to in par. 2.1.1, 7.2.2, 7.2.3 and 7.3 may be obtained from the Canadian General Standards Board, Sales Unit, Ottawa, Canada, K1A 1G6. Telephone (819) 956-0425 or 956-0426. Fax (819) 956-5644.
- 7.4.2 The publication referred to in par 2.1.2 may be obtained from the Canada Communication Group, Publishing, Ottawa, Canada K1A 0S9. Telephone (819) 956-4802.
- 7.4.3 The publication referred to in par. 2.1.3 may be obtained from ASTM, 1916 Race Street, Philadelphia, PA 19103, U.S.A. or from the Standards Council of Canada, Standards Sales Branch, 350 Sparks Street, Suite 1200, Ottawa, Ontario K1P 6N7.