



Government
of Canada

Gouvernement
du Canada

Canadian General
Standards Board Office des normes
générales du Canada

Series 1
Série des 1

WITHDRAWAL

October 2011

Selected standards in the series Paints, pigments and related products

These CGSB standards and National Standards of Canada are hereby withdrawn due to limited use and support for their revision.

The Standards Council of Canada requires that accredited Standards Development Organizations, such as the CGSB, regularly review a consensus Standard to determine whether to re-approve, revise or withdraw. The review cycle is normally five years from the publication date of the latest edition of the Standard.

The information contained in these Standards was originally developed pursuant to a voluntary standards development initiative of the CGSB. The information contained therein may no longer represent the most current, reliable, and/or available information on these subjects. CGSB hereby disclaims any and all claims, representation or warranty of scientific validity, or technical accuracy implied or expressed respecting the information therein contained. The CGSB shall not take responsibility nor be held liable for any errors, omissions, inaccuracies or any other liabilities that may arise from the provision or subsequent use of such information. These Standards are

RETRAIT

Octobre 2011

Sélection de normes de la série Peintures, pigments et produits connexes

Ces normes de l'ONGC et ces Normes nationales du Canada sont retirées par le présent avis en raison de leur utilisation limitée et du manque de support pour leur révision.

Le Conseil canadien des normes exige que les organismes accrédités d'élaboration de normes, tel que l'ONGC, effectue régulièrement un examen des normes consensuelles afin de déterminer s'il y a lieu d'en renouveler l'approbation, de les réviser ou de les retirer. Le cycle d'examen d'une norme est généralement de cinq ans à partir de la date de publication de la dernière édition de celle-ci.

L'information contenue dans ces normes a été élaborée initialement en vertu d'une initiative volontaire d'élaboration de normes de l'ONGC. Elle peut ne plus représenter l'information disponible et/ou l'information la plus actuelle ou la plus fiable à ce sujet. L'ONGC décline par la présente toute responsabilité à l'égard de toute affirmation, déclaration ou garantie de validité scientifique ou d'exactitude technique implicite ou explicite relative à l'information contenue dans ces normes. L'ONGC n'assumera aucune responsabilité et ne sera pas tenu responsable quant à toute erreur, omission, inexactitude ou autre conséquence pouvant découler de la fourniture ou de l'utilisation subséquente de

to be referred to for archival purposes only as their content has been repealed as of the date on this withdrawal notice.

Archived copies of withdrawn standards for historic or archival purposes are still available from the CGSB Sales Centre by telephone at 819-956-0425 or 1-800-665-2472, by fax at 819-956-5740, by Internet at www.tpsgc-pwgsc.gc.ca/ongc-cgsb/, by e-mail at ncr.CGSB-ONGC@tpsgc-pwgsc.gc.ca or by mail at Sales Centre, Canadian General Standards Board, 11 Laurier Street, Gatineau, Canada K1A 1G6.

CAN/CGSB-1.5-M91

Low Flash Petroleum Spirits Thinner
(ICS 87.040)

CAN/CGSB-1.28-98

Exterior Alkyd House Paint (ICS 87.040)

CAN/CGSB-1.36-97

General Purpose Interior Alkyd Varnish
(ICS 87.040)

CAN/CGSB-1.38-2000

Interior Enamel Undercoater (ICS 87.040)

CAN/CGSB-1.40-97

Anticorrosive Structural Steel Alkyd Primer
(ICS 87.040)

CAN/CGSB-1.57-2003

Interior Alkyd Semigloss Enamel
(ICS 87.040)

CAN/CGSB-1.59-97

Alkyd Exterior Gloss Enamel (ICS 87.040)

CAN/CGSB-1.60-97

Interior Alkyd Gloss Enamel (ICS 87.040)

cette information. Ces normes doivent être consultées à des fins archivistiques seulement puisque leur contenu a été révoqué à la date du présent avis de retrait.

Des copies archivées des normes retirées peuvent être obtenues à des fins historiques ou archivistiques auprès du Centre des ventes de l'ONGC. Il suffit d'en faire la demande par téléphone au 819-956-0425 ou 1-800-665-2472, par télécopieur au 819-956-5740, par Internet à : www.tpsgc-pwgsc.gc.ca/ongc-cgsb/, par courriel à ncr.CGSB-ONGC@tpsgc-pwgsc.gc.ca, ou par courrier adressé au Centre des ventes, Office des normes générales du Canada, 11, rue Laurier, Gatineau, Canada K1A 1G6.

CAN/CGSB-1.5-M91

Diluant, essence minérale à faible point d'éclair (ICS 87.040)

CAN/CGSB-1.28-98

Peinture aux résines alkydes d'extérieur pour bâtiments (ICS 87.040)

CAN/CGSB-1.36-97

Vernis d'intérieur aux résines alkydes d'usage général (ICS 87.040)

CAN/CGSB-1.38-2000

Peinture-émail d'intérieur, pour couche de fond (ICS 87.040)

CAN/CGSB-1.40-97

Peinture pour couche primaire anticorrosion, aux résines alkydes, pour acier de construction (ICS 87.040)

CAN/CGSB-1.57-2003

Peinture-émail, d'intérieur, semi-brillante, aux résines alkydes (ICS 87.040)

CAN/CGSB-1.59-97

Peinture-émail, d'extérieur, brillante, aux résines alkydes (ICS 87.040)

CAN/CGSB-1.60-97

Peinture-émail brillante d'intérieur aux résines alkydes (ICS 87.040)

CAN/CGSB-1.61-2004

Exterior and Interior Marine Alkyd Enamel
(ICS 87.040)

CAN/CGSB-1.69-98

Aluminum Paint (ICS 87.040)

1-GP-71 (Oct 1983)

Methods of Testing Paints and Pigments
(ICS 87.040)

1-GP-71

Methods of Testing Paints and Pigments

No. 5-96

Drying Times of Paints and Related
Coatings (ICS 87.040)

No. 38-96

Blushing Resistance of Lacquer
Finishes (ICS 87.040)

No. 73-96

Beilstein Test for Chlorinated Solvents
(ICS 87.040)

CAN/CGSB-1.73-97

Exterior and Interior Enamel for Floors
(ICS 87.040)

CAN/CGSB-1.74-2001

Alkyd Traffic Paint (ICS 87.040)

CAN/CGSB-1.76-2000

Interior and Exterior Heat-Resistant Enamel
(ICS 87.040)

CAN/CGSB-1.81-M90

Air Drying and Baking Alkyd Primer for
Vehicles and Equipment (ICS 87.040)

CAN/CGSB-1.84-M91

Alkyd Primer for Hardwood (ICS 87.040)

CAN/CGSB-1.61-2004

Peinture-émail aux résines alkydes,
d'extérieur et d'intérieur, marine
(ICS 87.040)

CAN/CGSB-1.69-98

Peinture à l'aluminium (ICS 87.040)

1-GP-71 (oct. 1983)

Méthodes d'essai des peintures et pigments
(ICS 87.040)

1-GP-71

Méthodes d'essai des peintures et pigments

N° 5-96

Durée de séchage des peintures et
revêtements apparentés (ICS 87.040)

N° 38-96

Résistance à l'opalescence des
produits-laque de finition (ICS 87.040)

N° 73-96

Détermination de la présence de
solvants chlorés par l'essai de Beilstein
(ICS 87.040)

CAN/CGSB-1.73-97

Peinture-émail d'extérieur et d'intérieur,
pour sols (ICS 87.040)

CAN/CGSB-1.74-2001

Peinture alkyde de démarcation routière
(ICS 87.040)

CAN/CGSB-1.76-2000

Peinture-émail résistant à la chaleur,
d'intérieur et d'extérieur (ICS 87.040)

CAN/CGSB-1.81-M90

Peinture pour couche primaire aux résines
alkydes, séchant à l'air ambiant et au four,
pour véhicules automobiles et équipement
(ICS 87.040)

CAN/CGSB-1.84-M91

Peinture d'impression aux résines alkydes,
pour bois dur (ICS 87.040)

CAN/CGSB-1.88-92

Gloss Alkyd Enamel, Air Drying and Baking
(ICS 87.040)

CAN/CGSB-1.100-99

Interior Flat Latex Paint (ICS 87.040)

CAN/CGSB-1.104-M91

Semigloss Alkyd Air Drying and Baking
Enamel (ICS 87.040)

CAN/CGSB-1.105-M91

Quick-Drying Primer (ICS 87.040)

CAN/CGSB-1.114-M91

Quick-Drying Flat Enamel (ICS 87.040)

CAN/CGSB-1.118-95

Interior Flat Alkyd Finish (ICS 87.040)

CAN/CGSB-1.119-2000

Interior Latex Primer-Sealer (ICS 87.040)

CAN/CGSB-1.122-99

Anticorrosive Vinyl Primer (ICS 87.040)

CAN/CGSB-1.132-M90

Zinc Chromate Primer, Low Moisture
Sensitivity (ICS 87.040)

CAN/CGSB-1.135-99

Flat Alkyd Enamel for Equipment
(ICS 87.040)

CAN/CGSB-1.138-97

Exterior Latex Flat Paint (ICS 87.040)

CAN/CGSB-1.143-98

Silicone Alkyd Heat-Resistant Aluminum
Enamel (ICS 87.040)

CAN/CGSB-1.88-92

Peinture-émail brillante aux résines alkydes,
séchant à l'air ambiant et au four
(ICS 87.040)

CAN/CGSB-1.100-99

Peinture-émulsion mate d'intérieur
(ICS 87.040)

CAN/CGSB-1.104-M91

Peinture-émail semi-brillante aux résines
alkydes séchant à l'air ambiant et au four
(ICS 87.040)

CAN/CGSB-1.105-M91

Peinture pour couche primaire à séchage
rapide (ICS 87.040)

CAN/CGSB-1.114-M91

Peinture-émail mate à séchage rapide
(ICS 87.040)

CAN/CGSB-1.118-95

Peinture de finition mate d'intérieur aux
résines alkydes (ICS 87.040)

CAN/CGSB-1.119-2000

Peinture-émulsion d'impression d'intérieur
(ICS 87.040)

CAN/CGSB-1.122-99

Peinture pour couche primaire, aux résines
vinyliques, anticorrosion (ICS 87.040)

CAN/CGSB-1.132-M90

Peinture pour couche primaire, au chromate
de zinc, à faible sensibilité à l'humidité
(ICS 87.040)

CAN/CGSB-1.135-99

Peinture-émail mate aux résines alkydes
pour équipement (ICS 87.040)

CAN/CGSB-1.138-97

Peinture-émulsion (latex) mate, d'extérieur
(ICS 87.040)

CAN/CGSB-1.143-98

Peinture-émail aux résines silicones-
alkydes résistante à la chaleur (ICS 87.040)

CAN/CGSB-1.145-97

Solvent-Based Pigmented Stain
(ICS 87.040)

CAN/CGSB-1.146-99

Cold Curing, Gloss Epoxy Coating
(ICS 87.040)

CAN/CGSB-1.150-M91

Clear Lacquer for Wood Furniture
(ICS 87.040)

CAN/CGSB-1.153-2000

High-Build, Gloss Epoxy Coating
(ICS 87.040)

CAN/CGSB-1.154-M89

Latex Type Paint for Concrete Floors
(ICS 87.040)

CAN/CGSB-1.158-M89

Cellulose Nitrate Primer, Modified Alkyd
Type (ICS 87.040)

CAN/CGSB-1.159-92

Acrylic Cellulose Nitrate Gloss Lacquer
(ICS 87.040)

CAN/CGSB-1.160-93

Low Gloss Acrylic Cellulose Nitrate
Lacquer (ICS 87.040)

CAN/CGSB-1.162-2004

Emulsion Coating for Stucco and Masonry
(ICS 87.040)

CAN/CGSB-1.165-2004

Cold-Curing Epoxy Primer (ICS 87.040)

CAN/CGSB-1.171-98

Inorganic Zinc Coating (ICS 87.040)

CAN/CGSB-1.175-97

Polyurethane Interior Coating (ICS 87.040)

CAN/CGSB-1.145-97

Teinture pigmentée à base de solvant
(ICS 87.040)

CAN/CGSB-1.146-99

Revêtement aux résines époxydiques,
durcissant à froid, brillant (ICS 87.040)

CAN/CGSB-1.150-M91

Vernis-laque pour meubles en bois
(ICS 87.040)

CAN/CGSB-1.153-2000

Revêtement par peinture aux résines
époxydiques, à pouvoir garnissant élevé,
brillant (ICS 87.040)

CAN/CGSB-1.154-M89

Peinture-émulsion (latex) pour sols en béton
(ICS 87.040)

CAN/CGSB-1.158-M89

Peinture-laque pour couche primaire, au
nitrate de cellulose et aux résines alkydes
modifiées (ICS 87.040)

CAN/CGSB-1.159-92

Produit-laque brillant à la résine acrylique et
au nitrate de cellulose (ICS 87.040)

CAN/CGSB-1.160-93

Peinture-laque aux résines acryliques et au
nitrate de cellulose, peu brillante
(ICS 87.040)

CAN/CGSB-1.162-2004

Revêtement de type émulsion pour stuc et
maçonnerie (ICS 87.040)

CAN/CGSB-1.165-2004

Peinture pour couche primaire aux résines
époxydiques, durcissant à froid
(ICS 87.040)

CAN/CGSB-1.171-98

Enduit au zinc minéral (ICS 87.040)

CAN/CGSB-1.175-97

Revêtement de polyuréthane d'intérieur
(ICS 87.040)

CAN/CGSB-1.176-2000

Interior Clear Moisture-Curing Polyurethane Coating (ICS 87.040)

CAN/CGSB-1.177-M91

Two-Component Polyurethane Coating, Resistant to Chalking and Yellowing (ICS 87.040)

1-GP-180Ma (Feb 1996)

Coating, Polyurethane, Two-Package, General Purpose (ICS 87.040)

CAN/CGSB-1.181-99

Ready-Mixed Organic Zinc-Rich Coating (ICS 87.040)

CAN/CGSB-1.183-99

Zinc-Rich Epoxy Coating (ICS 87.040)

CAN/CGSB-1.184-98

Coal Tar-Epoxy Coating (ICS 87.040)

CAN/CGSB-1.188-2004

Emulsion Filler for Masonry Block (ICS 87.040)

CAN/CGSB-1.189-2000

Exterior Alkyd Primer for Wood (ICS 87.040)

CAN/CGSB-1.190-M90

Sanding Type Primer Surfacer (ICS 87.040)

1-GP-191M (Apr 1980)

Enamel, Automotive Refinishing, Fast Drying, Gloss (ICS 87.040)

1-GP-192Ma (Feb 1985)

Deck Coating, Nonslip, Epoxy (ICS 87.040)

CAN/CGSB-1.176-2000

Revêtement de polyuréthane, d'intérieur, durci à l'humidité, non pigmenté (ICS 87.040)

CAN/CGSB-1.177-M91

Revêtement de polyuréthane, à deux constituants séparés, non jaunissant et non farinant (ICS 87.040)

1-GP-180Ma (févr. 1996)

Revêtement de polyuréthane, à deux constituants séparés, pour utilisation générale (ICS 87.040)

CAN/CGSB-1.181-99

Enduit riche en zinc, organique et préparé (ICS 87.040)

CAN/CGSB-1.183-99

Enduit aux résines époxydiques, riche en zinc (ICS 87.040)

CAN/CGSB-1.184-98

Revêtement à base de goudron de houille-résines époxydiques (ICS 87.040)

CAN/CGSB-1.188-2004

Apprêt-émulsion pour blocs de maçonnerie (ICS 87.040)

CAN/CGSB-1.189-2000

Peinture d'impression, d'extérieur, aux résines alkydes, pour le bois (ICS 87.040)

CAN/CGSB-1.190-M90

Peinture pour couche primaire surfaçante de type ponçable (ICS 87.040)

1-GP-191M (avr. 1980)

Peinture-émail brillante, à séchage rapide, pour le repeinturage des carrosseries de véhicules automobiles (ICS 87.040)

1-GP-192Ma (févr. 1985)

Revêtement de pont, antidérapant, aux résines époxydiques (ICS 87.040)

CAN/CGSB-1.193-99

High-Build Epoxy Marine Coating
(ICS 87.040)

CAN/CGSB-1.195-99

Interior Latex Semigloss Paint (ICS 87.040)

CAN/CGSB-1.198-2001

Cementitious Primer for Galvanized
Surfaces (ICS 87.040)

1-GP-200Ma (Jan 1985)

Deck Coating, Nonslip, Polyurethane
(ICS 87.040)

CAN/CGSB-1.202-2003

Interior Alkyd Low Gloss Enamel
(ICS 87.040)

CAN/CGSB-1.203-2003

Exterior Latex Wood Primer (ICS 87.040)

CAN/CGSB-1.204-98

Exterior Latex Pigmented Stain
(ICS 87.040)

CAN/CGSB-1.205-2003

Sealer for Application to Asbestos-Fibre
Releasing Materials (ICS 87.040)

CAN/CGSB-1.207-98

Low-Temperature Curing Epoxy Coating
(ICS 87.040)

CAN/CGSB-1.208-99

Marine Interior Water-Borne Gloss Enamel
(ICS 87.040)

CAN/CGSB-1.209-2003

Interior Latex Low Gloss Paint (ICS 87.040)

CAN/CGSB-1.210-2003

Quick-Drying Alkyd Primer for Structural
Steel (ICS 87.040)

CAN/CGSB-1.193-99

Revêtement aux résines époxydiques, à
pouvoir garnissant élevé, marin
(ICS 87.040)

CAN/CGSB-1.195-99

Peinture-émulsion semi-brillante d'intérieur
(ICS 87.040)

CAN/CGSB-1.198-2001

Peinture primaire additionnée de ciment,
pour surfaces galvanisées (ICS 87.040)

1-GP-200Ma (janv. 1985)

Revêtement de pont, antidérapant, aux
résines polyuréthannes (ICS 87.040)

CAN/CGSB-1.202-2003

Peinture-émail d'intérieur, aux résines
alkydes, peu brillante (ICS 87.040)

CAN/CGSB-1.203-2003

Peinture-émulsion (latex) d'impression
extérieure, pour bois (ICS 87.040)

CAN/CGSB-1.204-98

Teinture-émulsion pigmentée pour extérieur
(ICS 87.040)

CAN/CGSB-1.205-2003

Peinture d'obturation pour matériaux
renfermant des fibres d'amiant
(ICS 87.040)

CAN/CGSB-1.207-98

Revêtement aux résines époxydiques
durcissant à basse température
(ICS 87.040)

CAN/CGSB-1.208-99

Peinture-émail brillante en suspension
aqueuse, marine, d'intérieur (ICS 87.040)

CAN/CGSB-1.209-2003

Peinture-émulsion d'intérieur peu brillante
(ICS 87.040)

CAN/CGSB-1.210-2003

Peinture primaire aux résines alkydes à
séchage rapide pour acier de charpente
(ICS 87.040)

CAN/CGSB-1.211-95

Coating Systems for Marine Floating Navigational Aids (Buoys) (ICS 87.040)

CAN/CGSB-1.212-2004

Heavy-Metal-Free Marine Primer for Steel and Light-Alloy Surfaces (ICS 87.040)

CAN/CGSB-1.213-2004

Etch Primer (Pretreatment Coating or Tie Coat) for Steel and Aluminum (ICS 87.040)

CAN/CGSB-1.214-2004

Heavy-Metal-Free, Water-Borne, Marine Primer for Steel and Light-Alloy Surfaces (ICS 87.040)

CAN/CGSB-1.215-96

Two-Package Epoxy Blockfiller (ICS 87.040)

CAN/CGSB-1.216-97

Exterior Water-Borne Gloss Enamel (ICS 87.040)

CAN/CGSB-1.219-2001

Lead and Chromate-Free Waterborne Traffic Paint (ICS 87.040)

CAN/CGSB-1.220-2001

Lead and Chromate-Free Alkyd Traffic Paint (ICS 87.040)

CAN/CGSB-1.223-2004

Heavy-Metal-Free, Water-Borne Wash Primer-Tie Coat (ICS 87.040)

CAN/CGSB-1.300-2000

Applied Coating System of Semigloss Baked Finish for Metal Office Furniture (ICS 87.040)

CAN/CGSB-1.500-75

Methods for Test for Toxic Trace Elements in Protective Coatings (ICS 87.040)

CAN/CGSB-1.211-95

Systèmes de revêtement pour aides à la navigation flottantes (bouées) (ICS 87.040)

CAN/CGSB-1.212-2004

Peinture primaire sans métal lourd, marine, pour surfaces en acier et en alliage léger (ICS 87.040)

CAN/CGSB-1.213-2004

Peinture primaire réactive (enduit de traitement préliminaire ou couche de liaison) pour l'acier et l'aluminium (ICS 87.040)

CAN/CGSB-1.214-2004

Peinture primaire, sans métal lourd, en suspension aqueuse, marine, pour surfaces en acier et en alliage léger (ICS 87.040)

CAN/CGSB-1.215-96

Apprêt pour blocs aux résines époxydiques en deux constituants (ICS 87.040)

CAN/CGSB-1.216-97

Peinture-émail brillante d'extérieur en suspension aqueuse (ICS 87.040)

CAN/CGSB-1.219-2001

Peinture à l'eau de démarcation routière sans plomb ni chromate (ICS 87.040)

CAN/CGSB-1.220-2001

Peinture alkyde de démarcation routière sans plomb ni chromate (ICS 87.040)

CAN/CGSB-1.223-2004

Peinture primaire réactive – Couche de liaison, sans métal lourd, en suspension aqueuse (ICS 87.040)

CAN/CGSB-1.300-2000

Système de revêtement de finition semi-brillant, cuit au four, pour meubles métalliques de bureau (ICS 87.040)

CAN/CGSB-1.500-75

Méthodes d'essai des éléments toxiques à l'état de trace dans les revêtements protecteurs (ICS 87.040)

CAN/CGSB-1.501-M89

Method for Permeance of Coated
Wallboard (ICS 87.040)

CAN/CGSB-1.501-M89

Méthode de détermination de la perméance
des panneaux muraux revêtus (ICS 87.040)



Canadian
General
Standards
Board

CAN/CGSB-1.215-96

Two-Package Epoxy Blockfiller

Withdrawn/Retirée



National Standard of Canada

The CANADIAN GENERAL STANDARDS BOARD (CGSB), under whose auspices this National Standard of Canada has been developed is a government agency within Public Works and Government Services Canada. CGSB is engaged in the production of voluntary standards in a wide range of subject areas through the media of standards committees and the consensus process. The standards committees are composed of representatives of relevant interests including producers, consumers and other users, retailers, governments, educational institutions, technical, professional and trade societies, and research and testing organizations. Any given standard is developed on the consensus of views expressed by such representatives.

CGSB has been accredited by the Standards Council of Canada as a national standards-development organization. The standards that it develops and offers as National Standards of Canada conform to the criteria and procedures established for this purpose by the Standards Council of Canada. In addition to standards it publishes as national standards, CGSB produces standards to meet particular needs, in response to requests from a variety of sources in both the public and private sectors. Both CGSB standards and CGSB national standards are developed in conformance with the policies described in the CGSB Policy Manual for the Development and Maintenance of Standards.

CGSB standards are subject to review and revision to ensure that they keep abreast of technological progress. Suggestions for their improvement, which are always welcome, should be brought to the notice of the standards committees concerned. Changes to standards are issued either as separate amendment sheets or in new editions of standards.

An up-to-date listing of CGSB standards, including details on latest issues and amendments, and ordering instructions, is found in the CGSB Catalogue, which is published annually and is available without charge upon request. An electronic version, ECAT, is also available. Running on the Windows platform, it is updated quarterly. More information is available about CGSB products and services at our Web site — <http://w3.pwgsc.gc.ca/cgsb>.

Although the intended primary application of this standard is stated in its Scope, it is important to note that it remains the responsibility of the users of the standard to judge its suitability for their particular purpose.

The testing and evaluation of a product against this standard may require the use of materials and/or equipment that could be hazardous. This document does not purport to address all the safety aspects associated with its use. Anyone using this standard has the responsibility to consult the appropriate authorities and to establish appropriate health and safety practices in conjunction with any applicable regulatory requirements prior to its use. CGSB neither assumes nor accepts any responsibility for any injury or damage that may occur during or as the result of tests, wherever performed.

Attention is drawn to the possibility that some of the elements of this Canadian standard may be the subject of patent rights. CGSB shall not be held responsible for identifying any or all such patent rights. Users of this standard are expressly advised that determination of the validity of any such patent rights are entirely their own responsibility.

Further information on CGSB and its services and standards may be obtained from:

The Manager
Standardization Information Division
Canadian General Standards Board
Ottawa, Canada
K1A 1G6

The STANDARDS COUNCIL OF CANADA is the co-ordinating body of the National Standards System, a federation of independent, autonomous organizations working towards the further development and improvement of voluntary standardization in the national interest.

The principal objectives of the Council are to foster and promote voluntary standardization as a means of advancing the national economy, benefiting the health, safety and welfare of the public, assisting and protecting the consumer, facilitating domestic and international trade, and furthering international co-operation in the field of standards.

A National Standard of Canada is a standard which has been approved by the Standards Council of Canada and one which reflects a reasonable agreement among the views of a number of capable individuals whose collective interests provide, to the greatest practicable extent, a balance of representation of producers, users, consumers and others with relevant interests, as may be appropriate to the subject in hand. It normally is a standard that is capable of making a significant and timely contribution to the national interest.

Approval of a standard as a National Standard of Canada indicates that a standard conforms to the criteria and procedures established by the Standards Council of Canada. Approval does not refer to the technical content of the standard; this remains the continuing responsibility of the accredited standards-development organization.

Those who have a need to apply standards are encouraged to use National Standards of Canada whenever practicable. These standards are subject to periodic review; therefore, users are cautioned to obtain the latest edition from the organization preparing the standard.

The responsibility for approving National Standards of Canada rests with the:

Standards Council of Canada
45 O'Connor Street
Suite 1200
Ottawa, Ontario
K1P 6N7

How to order CGSB Publications:

- | | |
|--------------|---|
| by telephone | — (613) 941-8703 or
— 1-800-665-CGSB
(Canada only) |
| by fax | — (613) 941-8705 |
| by mail | — CGSB Sales Centre
Ottawa, Canada
K1A 1G6 |
| in person | — Suite 1402
222 Queen Street
Ottawa, Ontario |
| by email | — cgsb@piper.pwgsc.gc.ca |
| on the Web | — http://w3.pwgsc.gc.ca/cgsb |

TWO-PACKAGE EPOXY BLOCKFILLER

Prepared by the
Canadian General Standards Board 

Approved by the
Standards Council of Canada 

Published November 1996 by the
Canadian General Standards Board
Ottawa, Canada K1A 1G6

©Minister of Public Works and Government Services Canada — 1996

No part of this publication may be reproduced in any form without the prior permission of the publisher.

CANADIAN GENERAL STANDARDS BOARD
COMMITTEE ON CONSTRUCTION AND
MAINTENANCE COATINGS

(Membership at date of approval)

Benner, H.J.	<i>Chairperson</i>	Lanark Coating Services Ltd.
Abel, B.		ORTECH
Alvarez, E.		National Defence
Anacleto, P.		Lepage Ltd.
Andreassen, P.		Consolidated Coatings Corporation
Ankenmann, H.		Anchor Consultants Inc.
Araujo, T.		Triodem Technical Services Ltd.
Auger, A.		Public Works and Government Services Canada
Bailey, J.		Rohm & Haas Canada Inc.
Balmer, S.R.		ICI Paints (Canada) Inc.
Benoit, D.		Sico Inc.
Braund, V.		General Paint Ltd.
Cochrane, A.J.		Matchless Paints
Craan, A.G.		Health Canada
Desbiens, Y.		Stablex
Hamill, I.		Color Your World
Inch, J.		B.C. Hydro
Logan, B.		Swing Paints Ltd.
McCleery, Wm.T.		Valspar Inc.
Mocnaj, R.		International Paints (Canada) Ltd.
Patterson, W.J.		Standards Chemicals
Philipp, H.		Public Works and Government Services Canada
Philips, N.		National Defence
Poitras, Y.		Mills Paint and Wallcoverings
Pouw, Capt J.		National Defence
Raine, R.		Department of Transportation and Highways, British Columbia
Roberts, P.		The T. Eaton Company Canada Ltd.
Sanderson, R.W.		Laidlaw Environmental Services Ltd.
Smith, H.		Northern Paint Canada Inc.
Thornton, J.W.		Kub Coatings Corp.
Wiezoreck, G.		Master Painters & Decorators Association of British Columbia
Williams, R.		The Sherwin-Williams Co.
Craig, W.	<i>Secretary</i>	Canadian General Standards Board

Acknowledgment is made for the translation of this National Standard of Canada by the Translation Bureau of Public Works and Government Services Canada.

CANADIAN GENERAL STANDARDS BOARD

TWO-PACKAGE EPOXY BLOCKFILLER**1. SCOPE**

- 1.1 This standard applies to cold curing, two-package, solution type polyamide epoxy blockfiller intended for use on new or unpainted concrete block.
- 1.2 The testing and evaluation of a product against this standard may require the use of materials and/or equipment that could be hazardous. This document does not purport to address all the safety aspects associated with its use. Anyone using this standard has the responsibility to consult the appropriate authorities and to establish appropriate health and safety practices in conjunction with any applicable regulatory requirements prior to its use.

2. REFERENCED PUBLICATIONS

- 2.1 The following publications are referenced in this standard:

2.1.1 Canadian General Standards Board (CGSB)

1-GP-71 — Methods of Testing Paints and Pigments

CAN/CGSB-1.146 — Cold Curing, Gloss Epoxy Coating.

2.1.2 American Society for Testing and Materials (ASTM)

D1212 — Test Method for Wet Film Thickness of Organic Coatings

D 2697 — Test Method for Volume Nonvolatile Matter In Clear or Pigmented Coatings

D 3359 — Methods for Measuring Adhesion by Tape Test.

- 2.2 A reference to a regulation is always to the latest issue. A dated reference is to the issue specified. An undated reference is to the latest issue, unless otherwise specified by the authority applying this standard. The sources are given in the Notes section.

3. GENERAL REQUIREMENTS

- 3.1 The blockfiller shall be supplied as a two-component (two package) epoxy coating with adequately dispersed pigment.
- 3.2 The two components shall be capable of being readily mixed to a uniform condition by stirring, after being stored at temperatures ranging between 5 and 40°C in their original unopened containers for one year from date of shipment.
- 3.3 When the two components are mixed together according to the manufacturer's directions, the filler shall be suitable for application by brush, roller, or airless spray. The material shall roll on easily and evenly without coarse roller stipples.
- 3.4 When applied in accordance with the manufacturer's instructions, the filler shall fill voids adequately. Some lightweight block may require a second coat of filler to fill voids completely.

4. DETAILED REQUIREMENTS.

The blockfiller shall comply with the following detailed requirements when tested in accordance with the specified test methods:

		Test Method			
		Min.	Max.	CGSB 1-GP-71	ASTM
4.1	Dry to touch ¹	—	5 h	5	—
4.2	Dry to recoat and topcoat ¹	—	18 h	5	—
4.3	Dry hard, h ¹	—	48 h	5	—
4.4	Volume Solids	60%	—	—	D 2697
4.5	Gloss	—	85° Gloss Units	13.1 ²	—
4.6	Sag Resistance — When applied at a wet film thickness of 250 microns, the coating shall show no sign of sagging or flowing back over the uncoated area when tested in accordance with par. 6.2.1.				
4.7	Pot Life — When mixed according to the manufacturers directions and held at room temperature for 8 h, the block filler shall remain sprayable (par. 6.2.2).				
4.8	Adhesion — The blockfiller shall be applied to the smooth side of a concrete patio slab. It shall have a wet film thickness of 250 microns when tested according to ASTM D 1212. After curing for 7 d, it shall have an adhesion rating of not less than 4A when subjected to the X-cut tape test in accordance with ASTM D 3359, Method A. Use a tape which has a minimum strength of 4.5 N (1.0 pound) (eg. Scotch Brand acetate fibretape).				
4.9	Application Properties and Topcoat Compatibility — There shall be no blistering, wrinkling, sagging, softening, lifting, nor any other defects when a coating conforming to CAN/CGSB-1.146 is applied according to the manufacturer's instructions by spray over a film of blockfiller. The blockfiller shall be applied over a patio stone as in par. 4.8 and allowed to dry for 16 h.				

5. PREPARATION FOR DELIVERY

- 5.1 Unless otherwise specified (par. 7.1), preparation for delivery shall conform to normal commercial practice.
- 5.2 **Labelling** — In addition to complying with the labelling requirements of any relevant Acts or Regulations, each container shall be suitably labelled to show the following information:
- Name of material
- Standard number: CAN/CGSB-1.215-96
- Manufacturer's name and address
- Manufacturer's batch number
- Manufacturer's code number
- Instructions for use.

6. INSPECTION

- 6.1 **Sampling** — Sampling shall be carried out in accordance with CGSB standard 1-GP-71, Method 1.1.
- 6.2 **Testing**
- 6.2.1 **Sag Resistance** — Press a strip of 25 mm masking tape across the full width of a 100 × 200 mm cold rolled steel panel prepared according to CGSB standard 1-GP-71, Method 100.1. The tape shall be parallel to and centered on the shorter axis of the panel. Use separate panels for each coating of the system. Apply the material at the required thickness. Immediately after application, carefully remove the masking tape and stand the panel in a vertical position (with the bare strip horizontal). At the end of 4 h examine the panel for sagging or running of the coating into the bare area.
- 6.2.2 **Pot Life** — Fill a 3.78 L can with material which has been freshly mixed according to the manufacturer's instructions. Examine for consistency (par. 4.7) and then seal tightly and store under standard conditions (CGSB standard 1-GP-71, Method 103.1) for 8 h. Reexamine the material for consistency (par. 4.7).

¹ Applied at 250 microns (wet) (23°C and 50% RH.)

² Applied at 250 microns (wet) with cure time of 48 h.

7. NOTES

7.1 **Option** — The following option shall be specified in the application of this standard:

- a. Preparation for delivery, if other than as specified (par. 5.1).

7.2 Recommended Practice

7.2.1 Mix the material according to the manufacturer's instructions. Mixed material should be used within 8 h.

7.2.2 After mixing the two components together, follow the manufacturer's instructions for sweat-in time (induction time) before application.

7.2.3 The application temperature and humidity conditions shall be specified by the manufacturer, but under no conditions should the surface temperature be below 10°C.

7.3 Sources of Referenced Publications

7.3.1 The publications referred to in par. 2.1.1 may be obtained from the Canadian General Standards Board, Sales Centre, Ottawa, Canada K1A 1G6. Telephone (613) 941-8703 or 1-800-665-CGSB (Canada only). Fax (613) 941-8705.

7.3.2 The publications referred to in par. 2.1.2 may be obtained from the American Society for Testing and Materials, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959, U.S.A. or from the Standards Council of Canada, Standard Sales Branch, 45 O'Connor Street, Suite 1200, Ottawa, Ontario K1P 6N7.
