3-GP-40
31 December 1947
CANCELLATION
12 November 1965

CANADIAN GOVERNMENT SPECIFICATIONS BOARD

Specification
for

FLOOR OIL

CGSB Specification 3-GP-40, dated 31 December 1947, including Amendment No. 1, dated 31 December 1963, is cancelled as of 12 November 1965.

ARCHIVES COPY

ARCHIVES COPY

3-GP-40
31 December 1947
AMENDMENT NO. 1
31 December 1963

CANADIAN GOVERNMENT SPECIFICATIONS BOARD

Specification
for

OIL; FLOOR

TITLE* - Change to read:

FLOOR OIL

Withdrawn/Retirée

---

* This revised title is in accordance with NATO Codified Nomenclature.

3-GP-40
31 December 1947*
Supersedes DND 40

CANADIAN GOVERNMENT SPECIFICATIONS BOARD

Specification for OIL; FLOOR

1. DEFINITION

1.1 This specification applies to a pure, highly refined mineral oil.

2. GENERAL REQUIREMENTS

2.1 This oil shall be clear, bright and transparent. It shall be free from all suspended impurities and from objectionable odour.

3. DETAIL REQUIREMENTS

3.1 Physical and Chemical Requirements

	Min.	Max.	Test Method
Flash Point, °F.	300	-	27.1
Viscosity at 100°F.			
Kinematic, Centistokes	-	23.0	36.1
Approx. S.U. Seconds	-	110	36.2
Pour Point, °F.	-	+35	28.2
Total Acid Number	-	0.10	2.1 or 2.2
Color - Union	-	2	54.1

4. USES

4.1 OIL: FLOOR is intended for use in controlling dust and disease-producing organisms in barrack rooms.

---

* Reprinted 12 January 1953 with no change in technical requirements.

PRICE 10¢

Withdrawn/Retirée

5. METHODS OF SAMPLING AND TESTING

5.1 A sample of not less than one Imperial quart shall be provided for tests and shall be obtained in accordance with section 1.2 of Schedule No. 3-GP-0: Methods of Testing Petroleum and Associated Products.

5.2 The methods of testing shall in all cases be those described in Schedule No. 3-GP-0, using the procedure specified with each requirement.

Withdrawn/Retirée

Correspondence regarding this specification should be addressed to the Secretary, Canadian Government Specifications Board, National Research Council, OTTAWA, Canada.

REFERENCE COPY

No. 3-GP-40-1947
Issued 31 December, 1947
Supersedes D.N.D. 40

CANADIAN GOVERNMENT PURCHASING STANDARDS COMMITTEE

Specification for

OIL - FLOOR

A. DEFINITION

A-1 This specification applies to a pure, highly refined mineral oil.

B. GENERAL REQUIREMENTS

B-1 This oil shall be clear, bright and transparent. It shall be free from all suspended impurities and from objectionable odours.

C. DETAILED REQUIREMENTS

C-1 Physical and Chemical Requirements

	Min.	Max.	Test Method
Flash Point, °F.	300	-	27.1
Viscosity at 100°F.			
Kinematic, centistokes	-	23.0	36.1
Approx. S.U. Seconds	-	110	36.2
Pour Point, °F.	-	+35	28.2
Total Acid Number	-	0.10	2.1 or 2.2
Colour - Union	-	2	54.1

D. USES

D-1 OIL - FLOOR is intended for use in controlling dust and disease-producing organisms in Barrack Rooms.

E. METHODS OF SAMPLING AND TESTING

E-1 A sample of not less than one imperial quart shall be provided for tests and shall be obtained in accordance with section 1.2 of Schedule No. 3-GP-0: Methods of Testing Petroleum and Associated Products.

E-2 The methods of testing shall in all cases be those described in Schedule No. 3-GP-0, using the procedure specified with each requirement.

Correspondence regarding this specification should be addressed to the Secretary, Canadian Government Purchasing Standards Committee, National Research Council, OTTAWA, Canada.

Withdrawn/Retirée

REFERENCE COPY

D.N.D. 40
Issued 17 June, 1944.

Canadian Government Purchasing Standards Committee

Wartime Specification for

OIL - Floor

This specification may not be reproduced or published in any form without written authority.

A. GRADE

A-1 This oil shall be of one grade.

B. GENERAL REQUIREMENTS

B-1 This oil shall be a pure, highly refined mineral oil, and shall be clear, bright and transparent. It shall be free from all suspended impurities and from objectionable odours.

C. DETAILED REQUIREMENTS

C-1 Physical and Chemical Requirements.

	Min.	Max.	A.S.T.M. Test No.
Flash Point, °F.	300		D.92-33
Viscosity			
Kinematic at 100°F.		23.0	D.445-42T
Approx. Saybolt at 100°F.		110	D.88-38
Pour Point, °F.		+35	D.97-39
Neutralization No.		0.10	D.663-42T
Colour - Union		2	D.155-39T

D. INSPECTION AND TESTS

D-1 Unless otherwise specified, all tests shall be made according to the Standards or Tentative Standards of the American Society for Testing Materials (A.S.T.M.) as shown in C-1.

Withdrawn/Retirée

D-2 Approval of Product

In addition to meeting the above General and Detailed Requirements, the product must prove satisfactory in service. If found unsatisfactory, further use of the product may be discontinued. Decision regarding the suitability of the oil under service conditions rests with the Department of National Defence.

D-3 Invitation to Tender

The contractor shall furnish with his initial tender a typical analysis of the product he proposes to supply.

Shipments shall be made in accordance with terms specified in the acceptance of tender.

D-4 Analyses of Shipments

The contractor shall certify on the invoice covering each shipment that the product meets all the requirements of the specification under which it was purchased. In the event that the product supplied fails to meet the requirements of the specification, a rebate of 25% of the price charged will be required on that portion already used, and the balance will be returned to the contractor, at his own expense, for credit. The name of any contractor supplying products which do not conform to specifications required on tenders, may be deleted from the list of eligible contractors, until such time as the contractor can guarantee the supply of satisfactory products.

E. MARKING

Containers must be clearly and legibly stencilled as follows:-

D.N.D. 40,
Oil - Floor,
Name of Manufacturer
Date of Filling,
Quantity of Oil.

F. NOTES

F-1 Oil - Floor is intended for use in controlling dust and disease - producing organisms in Barrack Rooms.

F-2 Copies of this specification may be obtained from:-

The Secretary,
Canadian Government Purchasing Standards Committee,
National Research Council,
OTTAWA, Canada.

Withdrawn/Retiree