3-GP-64
CANCELLATION
22 February 1957

CANADIAN GOVERNMENT SPECIFICATIONS BOARD

Specification
for

OIL; LUBRICATING, BLACK, GENERAL PURPOSE

CGSB Specification 3-GP-64, dated 31 December 1947 is cancelled as of 22 February 1957.

3-GP-64
31 December 1947*
Supersedes 3-GP-4-2A1

CANADIAN GOVERNMENT SPECIFICATIONS BOARD

Specification for OIL; LUBRICATING, BLACK, GENERAL PURPOSE **

Withdrawn/Retirée

1. DEFINITION

1.1 This specification applies to a vacuum reduced long residue or of a blend of unblown bitumen and mineral oil.

2. GENERAL REQUIREMENTS

2.1 OIL; LUBRICATING, BLACK, GENERAL PURPOSE shall be homogeneous and free from water, suspended matter and sediment.

3. DETAIL REQUIREMENTS

3.1 Physical and Chemical Requirements

	Min.	Max.	Test Method
Flash Point, °F.	300	-	27.1
Viscosity at 210°F.			
Kinematic, Centistokes	10	13	36.1
Approx. S.U. Seconds	60	70	36.2
Pour Point, °F.	-	+45	28.3
Strong Acid Number	-	nil	2.1 or 2.2

---

* Reprinted 12 January, 1953 with no change in technical requirements.

** For other grades of Black, General Purpose Lubricating Oil see specifications 3-GP-94, 274, 661 and 662.

PRICE 10¢

4. USES

4.1 OIL; LUBRICATING, BLACK, GENERAL PURPOSE, is intended for the lubrication of chains, wire ropes, large open gears, and other heavy equipment.

5. METHODS OF SAMPLING AND TESTING

5.1 A sample of not less than one Imperial quart shall be provided for tests and shall be obtained in accordance with section 1.2 of Schedule No. 3-GP-0: Methods of Testing Petroleum and Associated Products.

5.2 The methods of testing shall in all cases be those described in Schedule No. 3-GP-0, using the procedure specified with each requirement.

Withdrawn/Retired

Correspondence regarding this specification should be addressed to the Secretary, Canadian Government Specifications Board, National Research Council, OTTAWA, Canada.