3-GP-450
31 December 1947
CANCELLATION
16 December 1966

CANADIAN GOVERNMENT SPECIFICATIONS BOARD

Specification
for

OIL; LUBRICATING, CYLINDER, COMPOUNDED

CGSB Specification 3-GP-450, dated 31 December 1947, is cancelled as of 16 December 1966.

ARCHIVES COPY

ARCHIVES COPY

3-GP-450
31 December, 1947
CORRECTION NO. 1
8 August, 1950

CANADIAN GOVERNMENT SPECIFICATIONS BOARD

Specification
for

OIL - LUBRICATING, CYLINDER, COMPOUNDED

A. DEFINITION

A-1 The last word of the definition should be "oil" not "acid".

i.e. "---------- suitable fatty oil."

Withdrawn/Retirée

No. 3-GP-450-1947
Issued 31 December, 1947
Supersedes 3-GP-4 -3B2

CANADIAN GOVERNMENT PURCHASING STANDARDS COMMITTEE

Specification for
OIL - LUBRICATING, CYLINDER, COMPOUNDED*

A. DEFINITION

A-1 OIL - LUBRICATING, CYLINDER, COMPOUNDED shall consist of a blend of refined mineral oil with 4 to 6 percent of suitable fatty acid.

B. GENERAL REQUIREMENTS

B-1 The finished product shall be homogeneous, stable, and free from visible impurities.

C. DETAILED REQUIREMENTS

C-1 Physical and Chemical Requirements

	Min.	Max.	Test Method
Fatty Oil Content, per cent	4	6	7.1
Flash Point, °F.	490	-	27.1
Viscosity at 210°F.			
Kinematic, Centistokes	30	34	36.1
Approx. S.U. Seconds	140	160	36.2
Pour Point, °F.	-	+60	28.2
Total Acid Number	-	0.5	2.1 or 2.2
Strong Acid Number	-	Nil	2.1 or 2.2
Precipation Number	-	0.05	6.1
Saponification Number	8.0	-	7.1
Carbon Residue, per cent	-	3.5	41.2
Corrosion	-	Negative	60.2

D. USES

D-1 OIL - LUBRICATING, CYLINDER, COMPOUNDED, is intended for the lubrication of cylinders and valve chests of non-condensing reciprocating steam engines using saturated steam at pressure below 200 lbs. per square inch.

* For other grades of Compounded Cylinder Lubricating Oil see Specifications 3-GP-440 and 3-GP-495.

Withdrawn/Retiree

E. METHODS OF SAMPLING AND TESTING

E-1 A sample of not less than one Imperial gallon shall be provided for tests and shall be obtained in accordance with section 1.2 of Schedule No. 3-GP-0: Methods of Testing Petroleum and Associated Products.

E-2 The methods of testing shall in all cases be those described in Schedule No. 3-GP-0, using the procedure specified with each requirement.

Withdrawn/Retirée

Correspondence regarding this specification should be addressed to the Secretary, Canadian Government Purchasing Standards Committee, National Research Council, OTTAWA, Canada.

No. 3-GP-450-1947
Issued 31 December, 1947
Supersedes 3-GP-4 -3B2

CANADIAN GOVERNMENT PURCHASING STANDARDS COMMITTEE

Specification for OIL - LUBRICATING, CYLINDER, COMPOUNDED*

A. DEFINITION

A-1 OIL - LUBRICATING, CYLINDER, COMPOUNDED shall consist of a blend of refined mineral oil with 4 to 6 percent of suitable fatty acid.

B. GENERAL REQUIREMENTS

B-1 The finished product shall be homogeneous, stable, and free from visible impurities.

C. DETAILED REQUIREMENTS

C-1 Physical and Chemical Requirements

	Min.	Max.	Test Method
Fatty Oil Content, per cent	4	6	7.1
Flash Point, °F.	490	-	27.1
Viscosity at 210°F.			
Kinematic, Centistokes	30	34	36.1
Approx. S.U. Seconds	140	160	36.2
Pour Point, °F.	-	+60	28.2
Total Acid Number	-	0.5	2.1 or 2.2
Strong Acid Number	-	Nil	2.1 or 2.2
Precipation Number	-	0.05	6.1
Saponification Number	8.0	-	7.1
Carbon Residue, per cent	-	3.5	41.2
Corrosion	-	Negative	60.2

D. USES

D-1 OIL - LUBRICATING, CYLINDER, COMPOUNDED, is intended for the lubrication of cylinders and valve chests of non-condensing reciprocating steam engines using saturated steam at pressure below 200 lbs. per square inch.

* For other grades of Compounded Cylinder Lubricating Oil see Specifications 3-GP-440 and 3-GP-495.

Withdrawn/Retiree

E. METHODS OF SAMPLING AND TESTING

E-1 A sample of not less than one Imperial gallon shall be provided for tests and shall be obtained in accordance with section 1.2 of Schedule No. 3-GP-0: Methods of Testing Petroleum and Associated Products.

E-2 The methods of testing shall in all cases be those described in Schedule No. 3-GP-0, using the procedure specified with each requirement.

Withdrawn/Retirée

Correspondence regarding this specification should be addressed to the Secretary, Canadian Government Purchasing Standards Committee, National Research Council, OTTAWA, Canada.