

5-GP-15  
June 1950  
CANCELLATION  
July 1972

CANADIAN GOVERNMENT SPECIFICATIONS BOARD

Specification  
for

LACING: LEATHER

This specifications is cancelled as of the above date because it is no longer being used for government purchasing.



# CANADIAN GOVERNMENT SPECIFICATIONS BOARD

SPECIFICATION

FOR

LACING; LEATHER

5-GP-15

23 JUNE 1950

ARCHIVES COPY

THIS SPECIFICATION APPLIES TO LEATHER LACING FROM  
VEGETABLE TANNED GOAT SKIN OR CALF SKIN

NATIONAL RESEARCH COUNCIL, OTTAWA, CANADA

Price

5 CENTS

For the convenience of those wishing to purchase publications of the Canadian Government Specifications Board, a coupon system has been introduced in order to make payment for these publications relatively simple. Coupons are available in denominations of 5c., 25c., and 50c. and may be obtained by forwarding a remittance to the National Research Council in the form of Bank, Express, or Post Office Money Order, or a cheque made payable at par in Ottawa, to Receiver General of Canada, credit National Research Council (stamps are not acceptable). These coupons can then be used when submitting orders for publications. An Index of Specifications can be obtained on request.

COMMITTEE ON SPECIFICATIONS FOR LEATHER

Breithaupt, L.O., M.P. (Chairman)      Breithaupt Leather Co. Limited.

SUBCOMMITTEE "C" ON GLOVE AND MISCELLANEOUS LEATHERS

|                             |                                                                        |
|-----------------------------|------------------------------------------------------------------------|
| Montgomery, K.L. (Chairman) | John A. Lang and Sons, Limited                                         |
| Beal, S.P.                  | Inspection Services,<br>Department of National Defence.                |
| Corbeil, E. *               | Tetrault Shoe, Limited                                                 |
| Delcellier, H.A., Lt. Col.  | Dir. Inter-Service Development,<br>Department of National Defence.     |
| Edmonds, F.                 | Wickett and Craig, Limited.                                            |
| Fricke, G.                  | Clarke and Clarke Co. Limited.                                         |
| Hart, H.W.                  | Canadian Commercial Corporation                                        |
| Henry, W.C.                 | Ontario Research Foundation.                                           |
| Kramer, M.R. *              | Consumers Glove Co. Limited                                            |
| Lang, J. *                  | The Lang Tanning Co. Limited                                           |
| Leggatt, J.M.               | Jas. R. Kendall Leather Co.                                            |
| Lucas, H.                   | Edwards and Edwards, Limited.                                          |
| MacFeeters, E.              | Accommodation, Purchasing & Stores,<br>Department of Veterans Affairs. |
| Sayers, R.E.                | Canadian Commercial Corporation.                                       |
| Watterud, E.T. (Secretary)  | CGSB/National Research Council                                         |

\*Ex Officio members as Chairmen of other Leather Subcommittees.

23 June, 1950.

## CANADIAN GOVERNMENT SPECIFICATIONS BOARD

Specification  
forLACING; LEATHER1. DEFINITION

1.1 This specification applies to leather lacing, from vegetable tanned goat skin or calf skin.

2. APPLICABLE REGULATIONS

2.1 In the event of any inconsistency in contract documents, specification, drawings and/or patterns, the aforementioned shall prevail in the following manner:

- 2.1.1 Contract
- 2.1.2 Specification
- 2.1.3 Drawings
- 2.1.4 Pattern or sealed sample.

3. GENERAL REQUIREMENTS

3.1 The leather lacing covered by this specification shall be cut from leather which is free from imperfections or blemishes that may affect its appearance or serviceability, and in all respects not covered by this specification or contract documents, shall be equivalent to the sealed sample.

3.2 The lacing shall be cut from leather which is free from cuts, open scratches, deep wrinkles, and loose flesh.

3.3 The lacing shall be circular cut, bevelled, and in continuous lengths.

4. DETAIL REQUIREMENTS

4.1 Widths - The lacing shall be available in widths of  $5/64$ ",  $3/32$ ",  $1/8$ ", unless otherwise requested by the purchaser.

4.2 Tensile Strength - The lacing shall have a tensile strength, according to width, not less than the values indicated in Table I.

TABLE ITensile Strength

| Width<br>(Inches) | Minimum Breaking<br>Load (lb.) |
|-------------------|--------------------------------|
| $5/64$            | 5                              |
| $3/32$            | 7                              |
| $1/8$             | 9                              |

4.3 Elongation - The elongation, at a load of one-half the value specified in Table I, shall be not greater than 20 percent.

5. INSPECTION, SAMPLING, AND TEST METHODS

5.1 Methods of sampling and testing shall be in accordance with the American Leather Chemists Association, "Methods of Sampling and Analysis".

Withdrawn/Retirée

---

Correspondence regarding this specification should be addressed to the Secretary, Canadian Government Specifications Board, National Research Council, OTTAWA, Canada.